
Rubber, vulcanized or thermoplastic — Resistance to weathering

*Caoutchouc vulcanisé ou thermoplastique — Résistance aux
intempéries*

STANDARDSISO.COM : Click to view the full PDF of ISO 4665:2016



STANDARDSISO.COM : Click to view the full PDF of ISO 4665:2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Exposure to direct weathering, to weathering using glass-filtered daylight or to intensified weathering by daylight using Fresnel mirrors	2
6 Exposure to laboratory light sources	2
7 Changes in colour	3
7.1 Apparatus	3
7.1.1 Instrumental assessment	3
7.1.2 Visual assessment	3
7.2 Test piece	3
7.3 Procedure	3
7.3.1 General	3
7.3.2 Instrumental assessment	3
7.3.3 Visual assessment	3
8 Changes in other appearance properties	3
9 Changes in physical properties	3
9.1 General	3
9.2 Apparatus	4
9.3 Test pieces	4
9.4 Procedure	4
10 Expression of results	4
10.1 Change in colour	4
10.1.1 Instrumental measurements	4
10.1.2 Visual measurements	4
10.2 Changes in other appearance properties	5
10.3 Changes in physical properties	5
11 Test report	6
Annex A (informative) Weathering reference materials	7
Annex B (informative) Some properties which can be determined to assess change after exposure	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This third edition cancels and replaces the second edition (ISO 4665:2006), which has been technically revised with the following changes:

- normative references have been updated, small editorial changes made for clarification and compression set added to mechanical properties that could be measured.

Introduction

A number of different exposure techniques can be used to provide information on the effects of environmental stresses such as light, heat, and water on rubbers. Each of these has its own particular application and relevance. Explanation of, and guidance on, methods for exposure to natural and artificial weathering is given in ISO 877-1 and ISO 4892-1. Particular guidance on exposure to determine resistance to ozone is given in ISO 1431-1. The methods for exposure to weathering standardized for plastic materials are essentially suitable for rubbers, and hence this International Standard refers to the relevant ISO standards for plastics for the apparatus and procedures.

It is desirable that the procedures for the determination of changes in properties are the same whatever exposure is used and that the results should be expressed in a uniform manner. Such procedures are specified in this International Standard.

Exposure to weathering alters the properties of the material, particularly in the surface layer. The test method used to determine changes in properties should be selected after consideration of the properties of the material which are important in its proposed application and taking into account the fact that degradation might be concentrated at the surface layer. The methods chosen ought to be capable of measuring change in properties with sufficient precision within the ranges which are important in practice, so as to provide significant criteria of change.

STANDARDSISO.COM : Click to view the full PDF of ISO 4665:2016

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 4665:2016

Rubber, vulcanized or thermoplastic — Resistance to weathering

1 Scope

This International Standard specifies methods for the exposure of vulcanized or thermoplastic rubbers to natural or artificial weathering and methods for the determination of changes in colour, appearance, and physical properties resulting from exposure.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 877-1:2009, *Plastics — Methods of exposure to solar radiation — Part 1: General guidance*

ISO 877-2:2009, *Plastics — Methods of exposure to solar radiation — Part 2: Direct weathering and exposure behind window glass*

ISO 877-3:2009, *Plastics — Methods of exposure to solar radiation — Part 3: Intensified weathering using concentrated solar radiation*

ISO 1431-1, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static and dynamic strain testing*

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

ISO 4892-4, *Plastics — Methods of exposure to laboratory light sources — Part 4: Open-flame carbon-arc lamps*

ISO 18314-1, *Analytical colorimetry — Part 1: Practical colour measurement*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 877 and ISO 4892 and the following apply.

3.1 control

material exposed alongside the test material for comparison

Note 1 to entry: The control, for example, may be a material of similar or related composition to the test material or a material having a known response to the exposure conditions.

3.2

file test piece

portion of the material to be tested which is stored under conditions in which it is stable and is used for comparison between the exposed and the original state

3.3

masked area

portion of the exposed test piece which is protected from light exposure by masking

3.4

weathering reference material

reference material whose weathering degradation properties are well documented and repeatable when exposed to identical conditions

3.5

exposure stage

interval of exposure between determinations of change in properties, expressed as time or radiant exposure

4 Principle

Test pieces are exposed to natural or artificial weathering and the resulting changes in colour, appearance, and selected physical properties are determined.

5 Exposure to direct weathering, to weathering using glass-filtered daylight or to intensified weathering by daylight using Fresnel mirrors

Carry out the exposure in accordance with the relevant method of ISO 877, with the following additions and modifications:

- For tests under strain, prepare the test pieces and place them under strain in accordance with ISO 1431-1.
- It is recommended that one or more of the weathering reference materials described in [Annex A](#) be used as a control, the material selected depending on the type of rubber compound under test. The effects of natural weathering on these materials in a range of climates are detailed in Reference [\[1\]](#) and Reference [\[2\]](#).
- Condition the test pieces in accordance with ISO 23529.

6 Exposure to laboratory light sources

Carry out the exposure in accordance with ISO 4892-1 and, as relevant, ISO 4892-2, ISO 4892-3, or ISO 4892-4, with the following additions and modifications:

For tests under strain, prepare the test pieces and place them under strain in accordance with ISO 1431-1.

It is recommended that one or more of the weathering reference materials described in [Annex A](#) be used as a control, the material selected depending on the type of rubber compound under test. The effects of natural weathering on these materials in a range of climates are detailed in Reference [\[1\]](#) and Reference [\[2\]](#).

Condition the test pieces in accordance with ISO 23529.

NOTE 1 The general guidance on weathering of plastics given in ISO 4892-1 is applicable to rubbers.

NOTE 2 In general, an open-flame carbon-arc lamp is not recommended because it is not representative of sunlight.

7 Changes in colour

7.1 Apparatus

7.1.1 Instrumental assessment

Use a colour or colour change apparatus meeting the requirements described in ISO 18314-1.

7.1.2 Visual assessment

Use the grey scale in accordance with ISO 105-A02.

7.2 Test piece

The test piece shall be in any form which allows sufficient flat area for the determination of colour change.

NOTE It is convenient to use a test piece required for the determination of change in physical properties.

7.3 Procedure

7.3.1 General

The choice of instrumental or visual assessment of colour change shall be made by agreement between the interested parties.

7.3.2 Instrumental assessment

Measure the colour of the test piece before and after each exposure stage in general accordance with ISO 18314-1. If required, also measure the colour of a file test piece or a masked area.

7.3.3 Visual assessment

Compare the contrast rating of the exposed test piece and an unexposed file test piece, and if required, a masked area, after each exposure stage, in accordance with the procedure given in ISO 105-A02.

8 Changes in other appearance properties

Examine each test piece visually after each exposure stage for changes in appearance using, if appropriate, the procedure given in a relevant International Standard. Some examples of parameters used to assess change in appearance are listed in [Annex B](#).

Ozone cracking shall be assessed in accordance with ISO 1431-1.

NOTE Cracking or crazing in rubber test pieces exposed outdoors can result from light ageing as well as from ozone attack. A distinction is not always possible, particularly with light-coloured rubbers. Sunlight crazing is characterized by shallow cracks and usually occurs independently of strain, whereas a threshold strain has to be exceeded for ozone cracking to occur. Where there is doubt, it is useful to expose an unstrained test piece alongside the strained test piece for comparison.

9 Changes in physical properties

9.1 General

The properties measured may be those specified in an International Standard for the material or as agreed between the interested parties. Some suitable properties are listed in [Annex B](#).

9.2 Apparatus

Apparatus in accordance with the relevant International Standard for the determination of the properties shall be used.

9.3 Test pieces

Test pieces shall comply with the requirements of the relevant International Standard for the determination of the properties chosen.

Test pieces may be cut from an exposed sheet of material. In such cases, the test pieces shall be taken not less than 20 mm from any fixtures holding the material or from supports that are not intended to simulate the conditions of exposure of the material in service. In no circumstances shall any of the material be removed from the exposed face during test piece preparation.

9.4 Procedure

Condition the test pieces and carry out the property determination in accordance with the procedure given in the relevant International Standard. Determine the initial properties on unexposed test pieces and the properties of exposed test pieces after each exposure stage. If required, also determine the properties of file test pieces or masked areas.

Repeat the measurements carried out on the sample test pieces on test pieces from any control being used.

NOTE With some tests, the results will depend on which side of the test piece is exposed. For example, in tests involving bending or flexure, the result depends on whether the exposed or unexposed surface is placed under tension.

10 Expression of results

10.1 Change in colour

10.1.1 Instrumental measurements

Determine the colour difference in accordance with ISO 18314-1.

10.1.2 Visual measurements

Record the contrast rating of the test pieces which have been compared. If the observed contrast lies between two ratings on the grey scale, record an intermediate rating. For example, a rating of 3-4 signifies that the contrast is greater than 3 but less than 4.

Also, record the type of colour change using the following terms:

Hue	More blue or less blue
	More green or less green
	More red or less red
	More yellow or less yellow
Purity	Brighter
	Duller
Lightness	Lighter
	Darker

A typical report of colour change by visual assessment would be: "More yellow, duller, lighter, grey scale 2-3".

10.2 Changes in other appearance properties

For quantitative methods, calculate the change in property from:

$$C = P - P_x \quad (1)$$

where

P is the initial property;

P_x is the property at exposure stage x .

For qualitative methods, express the result on a scale agreed between the interested parties. The following is recommended for properties other than ozone cracking:

0	none
1	barely perceptible
2	moderate
3	substantial

NOTE This scale is arbitrary and, although it is of considerable value when assessing several test pieces at the same time, great care is necessary in interpreting results from different observations.

Surface cracking on test pieces exposed under strain shall be assessed for resistance to ozone in accordance with ISO 1431-1.

10.3 Changes in physical properties

Calculate the result of each measurement in accordance with the test method in the relevant International Standard. The change in property from the initial or file test piece value, P , to the post-exposure value, P_x , may be expressed in one of the following ways:

- a) as a percentage of the initial or file value:

$$\frac{P_x}{P} \times 100$$

- b) as the change in the property:

$$P - P_x$$

- c) the change as a percentage of the initial or file value:

$$\frac{P - P_x}{P} \times 100$$

- d) as a plot of the property against the time of exposure or the radiant exposure.

11 Test report

The test report shall include the following information:

- a) a reference to this International Standard, i.e. ISO 4665;
- b) the sample details:
 - 1) a full description of the sample and its origin,
 - 2) details of the compound and the cure conditions, where appropriate,
 - 3) the method of preparation of the test pieces,
 - 4) details of the use of file test pieces or masked areas, if relevant, and
 - 5) details of any weathering reference material or other control used;
- c) the test details:
 - 1) references to the relevant test method standards for determination of the changes in properties,
 - 2) the type of exposure and the apparatus used,
 - 3) the location and details of the exposure site for natural weathering, if relevant,
 - 4) a complete description of the exposure cycle or exposure conditions used,
 - 5) the procedure used to determine the exposure stages,
 - 6) whether the test pieces were placed under strain and, if so, the degree of strain,
 - 7) the nature of any backing, support or attachments used,
 - 8) the conditions of storage of the file test pieces, if relevant,
 - 9) the method used to determine the radiant exposure, if relevant,
 - 10) details of washing, if relevant, and
 - 11) any deviations from the standard procedures;
- d) the test results:
 - 1) the exposure stages, expressed as time or radiant exposure,
 - 2) the climatic data and/or radiant exposure,
 - 3) the colour changes, if relevant,
 - 4) other changes in appearance, if relevant,
 - 5) the resistance to cracking in the case of test pieces exposed under strain,
 - 6) the individual values obtained for each property measured,
 - 7) the test result at each exposure stage for each property measured, and
 - 8) the change in each property measured and the units in which the property is expressed;
- e) the date of the test.

Annex A (informative)

Weathering reference materials

A.1 General

This annex describes weathering reference materials which may be used for preparing control test pieces for assessing changes in physical properties in natural and artificial weathering.

A.2 Types of rubber

Four types of compound, using SBR, EPDM, CR, and NR, are given in [Table A.1](#) to [Table A.4](#).

In a correlation study conducted by Japanese experts, these four rubbers showed superior performance as weathering reference materials. In particular, SBR gave the most linear relationship between exposure and the changes in various properties.

It was also observed in the study that the changes in 100 % modulus and elongation at break showed a gradual change, even in a three-year outdoor exposure.

Consequently, it was found that there was a significant correlation between outdoor exposure testing and exposure testing with laboratory light sources for these four rubbers.

Other compounds were also studied (see Reference [1]) but are not recommended. Carbon black compounds without antioxidants showed a large change after a three-year outdoor exposure, but only a small change with laboratory light sources. Non-black compounds showed a large performance change in the early stages of weathering tests, but did not give suitable results in long-term exposures.

A.3 Composition

The compositions of these compounds are shown in [Table A.1](#) to [Table A.4](#).

Table A.1 — Composition of SBR compound

Ingredients	Parts by mass
SBR1502	100
Carbon black, N330	50
Zinc oxide	3
Stearic acid	1
Antioxidant, 6PPD ^a	2
Antioxidant, TMQ ^b	2
Wax ^c	1
Accelerator, TBBS ^d	1
Sulfur	1,75
Vulcanization: 160 °C, 25 min	
^a N-1,3-dimethylbutyl- <i>N'</i> -phenyl- <i>p</i> -phenylenediamine. ^b Polymerized 2,2,4-trimethyl-1,2-dihydroquinoline. ^c Melting point: 65 °C; density: 0,93 Mg/m ³ . ^d N-tert-butylbenzothiazole-2-sulfenamide.	

Table A.2 — Composition of EPDM compound

Ingredients	Parts by mass
EPDM ^a	100
Carbon black, N330	80
Zinc oxide	5
Stearic acid	1
Paraffinic process oil ^b	50
Antioxidant, TMQ ^c	2
Accelerator, TMTD ^d	1
Accelerator, MBT ^e	0,5
Sulfur	1,5
Vulcanization: 160 °C, 20 min	
^a EP24 [Mooney viscosity ML1+4 (100 °C): 65; ethylene content (mass %): 54; ENB termonomer content (mass %): 4,5] from JSR Corporation, or equivalent. ^b Diana PW90 process oil [viscosity (98,9 °C): 11,25 cSt; pour point: -15 °C; aniline point: 127,7 °C; density: 0,87 Mg/m ³] from Idemitsu Kosan Corporation, or equivalent. ^c Polymerized 2,2,4-trimethyl-1,2-dihydroquinoline. ^d Tetramethylthiuram disulfide. ^e 2-Mercaptobenzothiazole.	