

NFPA® 290

Standard for Fire Testing of Passive Protection Materials for Use on LP-Gas Containers

2013 Edition



NFPA, 1 Batterymarch Park, Quincy, MA 02169-7471
An International Codes and Standards Organization

IMPORTANT NOTICES AND DISCLAIMERS CONCERNING NFPA® DOCUMENTS
NOTICE AND DISCLAIMER OF LIABILITY CONCERNING THE USE OF NFPA DOCUMENTS

NFPA® codes, standards, recommended practices, and guides (“NFPA Documents”), of which the document contained herein is one, are developed through a consensus standards development process approved by the American National Standards Institute. This process brings together volunteers representing varied viewpoints and interests to achieve consensus on fire and other safety issues. While the NFPA administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in NFPA Documents.

The NFPA disclaims liability for any personal injury, property or other damages of any nature whatsoever, whether special, indirect, consequential or compensatory, directly or indirectly resulting from the publication, use of, or reliance on NFPA Documents. The NFPA also makes no guaranty or warranty as to the accuracy or completeness of any information published herein.

In issuing and making NFPA Documents available, the NFPA is not undertaking to render professional or other services for or on behalf of any person or entity. Nor is the NFPA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances.

The NFPA has no power, nor does it undertake, to police or enforce compliance with the contents of NFPA Documents. Nor does the NFPA list, certify, test, or inspect products, designs, or installations for compliance with this document. Any certification or other statement of compliance with the requirements of this document shall not be attributable to the NFPA and is solely the responsibility of the certifier or maker of the statement.

REMINDER: UPDATING OF NFPA DOCUMENTS

Users of NFPA codes, standards, recommended practices, and guides (“NFPA Documents”) should be aware that NFPA Documents may be amended from time to time through the issuance of Tentative Interim Amendments or corrected by Errata. An official NFPA Document at any point in time consists of the current edition of the document together with any Tentative Interim Amendment and any Errata then in effect.

In order to determine whether an NFPA Document has been amended through the issuance of Tentative Interim Amendments or corrected by Errata, visit the Document Information Pages on NFPA’s website. The Document Information Pages provide up-to-date, document specific information including any issued Tentative Interim Amendments and Errata.

To access the Document Information Page for a specific NFPA Document go to <http://www.nfpa.org/document> for a list of NFPA Documents, and click on the appropriate Document number (e.g., NFPA 101). In addition to posting all existing Tentative Interim Amendments and Errata, the Document Information Page also includes the option to sign-up for an “Alert” feature to receive an email notification when new updates and other information are posted regarding the document.

IMPORTANT NOTICES AND DISCLAIMERS CONCERNING NFPA® DOCUMENTS

ADDITIONAL NOTICES AND DISCLAIMERS

Updating of NFPA Documents

Users of NFPA codes, standards, recommended practices, and guides (“NFPA Documents”) should be aware that these documents may be superseded at any time by the issuance of new editions or may be amended from time to time through the issuance of Tentative Interim Amendments. An official NFPA Document at any point in time consists of the current edition of the document together with any Tentative Interim Amendments and any Errata then in effect. In order to determine whether a given document is the current edition and whether it has been amended through the issuance of Tentative Interim Amendments or corrected through the issuance of Errata, consult appropriate NFPA publications such as the National Fire Codes® Subscription Service, visit the NFPA website at www.nfpa.org, or contact the NFPA at the address listed below.

Interpretations of NFPA Documents

A statement, written or oral, that is not processed in accordance with Section 6 of the Regulations Governing Committee Projects shall not be considered the official position of NFPA or any of its Committees and shall not be considered to be, nor be relied upon as, a Formal Interpretation.

Patents

The NFPA does not take any position with respect to the validity of any patent rights referenced in, related to, or asserted in connection with an NFPA Document. The users of NFPA Documents bear the sole responsibility for determining the validity of any such patent rights, as well as the risk of infringement of such rights, and the NFPA disclaims liability for the infringement of any patent resulting from the use of or reliance on NFPA Documents.

NFPA adheres to the policy of the American National Standards Institute (ANSI) regarding the inclusion of patents in American National Standards (“the ANSI Patent Policy”), and hereby gives the following notice pursuant to that policy:

NOTICE: The user’s attention is called to the possibility that compliance with an NFPA Document may require use of an invention covered by patent rights. NFPA takes no position as to the validity of any such patent rights or as to whether such patent rights constitute or include essential patent claims under the ANSI Patent Policy. If, in connection with the ANSI Patent Policy, a patent holder has filed a statement of willingness to grant licenses under these rights on reasonable and nondiscriminatory terms and conditions to applicants desiring to obtain such a license, copies of such filed statements can be obtained, on request, from NFPA. For further information, contact the NFPA at the address listed below.

Law and Regulations

Users of NFPA Documents should consult applicable federal, state, and local laws and regulations. NFPA does not, by the publication of its codes, standards, recommended practices, and guides, intend to urge action that is not in compliance with applicable laws, and these documents may not be construed as doing so.

Copyrights

NFPA Documents are copyrighted. They are made available for a wide variety of both public and private uses. These include both use, by reference, in laws and regulations, and use in private self-regulation, standardization, and the promotion of safe practices and methods. By making these documents available for use and adoption by public authorities and private users, the NFPA does not waive any rights in copyright to these documents.

Use of NFPA Documents for regulatory purposes should be accomplished through adoption by reference. The term “adoption by reference” means the citing of title, edition, and publishing information only. Any deletions, additions, and changes desired by the adopting authority should be noted separately in the adopting instrument. In order to assist NFPA in following the uses made of its documents, adopting authorities are requested to notify the NFPA (Attention: Secretary, Standards Council) in writing of such use. For technical assistance and questions concerning adoption of NFPA Documents, contact NFPA at the address below.

For Further Information

All questions or other communications relating to NFPA Documents and all requests for information on NFPA procedures governing its codes and standards development process, including information on the procedures for requesting Formal Interpretations, for proposing Tentative Interim Amendments, and for proposing revisions to NFPA documents during regular revision cycles, should be sent to NFPA headquarters, addressed to the attention of the Secretary, Standards Council, NFPA, 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101; email: stds_admin@nfpa.org

For more information about NFPA, visit the NFPA website at www.nfpa.org.

Copyright © 2013 National Fire Protection Association®. All Rights Reserved.

NFPA® 290

Standard for

**Fire Testing of Passive Protection Materials
for Use on LP-Gas Containers**

2013 Edition

This edition of NFPA 290, *Standard for Fire Testing of Passive Protection Materials for Use on LP-Gas Containers*, was prepared by the Technical Committee on Fire Tests. It was issued by the Standards Council on November 27, 2012, with an effective date of December 17, 2012, and supersedes all previous editions.

This edition of NFPA 290 was approved as an American National Standard on December 17, 2012.

Origin and Development of NFPA 290

Although the 2003 edition was the first edition of NFPA 290, *Fire Testing of Passive Protection Materials for Use on LP-Gas Containers*, a test procedure for torch fire and hose stream testing of thermal insulating systems for LP-Gas containers has been included as an annex to NFPA 58, *Liquefied Petroleum Gas Code*, since the 1986 edition of that code. That test method was developed by the Technical Committee on Fire Tests at the request of the Technical Committee on Liquefied Petroleum Gases as a result of numerous BLEVE incidents that had occurred in previous years. In the mid-1990s, the test procedure saw greater use, particularly outside the United States, and the two technical committees agreed that it should be developed and maintained as a fire test standard under the scope of the Fire Test Committee rather than as an annex to NFPA 58.

The 2003 edition of NFPA 290 represented a refinement of the test procedure that previously appeared as an appendix to NFPA 58, and it reorganized the procedure as a stand-alone fire test standard using mandatory language in accordance with the *Manual of Style for NFPA Technical Committee Documents*.

The 2009 edition contained revisions to clarify its scope and purpose, and a revised definition of the term “passive fire protection material.”

The 2013 edition has been updated to reference the most up-to-date standards and terminology.

Technical Committee on Fire Tests

Barry L. Badders, Jr., *Chair*
Southwest Research Institute, TX [RT]

Farid Alfawakhiri, American Iron and Steel Institute, IL [M]
Jesse J. Beitel, Hughes Associates, Inc., MD [SE]
Rhonda P. Byrne, QAI Laboratories, CA [RT]
Gordon H. Damant, Inter-City Testing & Consulting Corp. of California, CA [SE]
William E. Fitch, Phyrefish.com, FL [SE]
Marcelo M. Hirschler, GBH International, CA [SE]
Alfred J. Hogan, Winter Haven, FL [E]
Rep. International Fire Marshals Association
Paul A. Hough, Armstrong World Industries, Inc., PA [M]
Mohammed M. Khan, FM Global, MA [I]
William E. Koffel, Koffel Associates, Inc., MD [SE]
Richard T. Long, Jr., Exponent, Inc., MD [M]
Rep. Upholstered Furniture Action Council

Michael E. Luna, Intertek Testing Services, TX [RT]
Andre W. Marshall, University of Maryland, MD [SE]
Rodney A. McPhee, Canadian Wood Council, Canada [M]
Kathleen A. Newman, Firetect, CA [M]
David T. Sheppard, U.S. Bureau of Alcohol, Tobacco, Firearms & Explosives, MD [RT]
Dwayne E. Sloan, Underwriters Laboratories Inc., NC [RT]
Kuma Sumathipala, American Forest & Paper Association, DC [M]
Rick Thornberry, The Code Consortium, Inc., CA [SE]
Robert A. Wessel, Gypsum Association, MD [M]

Alternates

Scott W. Adams, Park City Fire Service District, UT [E]
(Alt. to A. J. Hogan)
Erik H. Anderson, Koffel Associates, Inc., MD [SE]
(Alt. to W. E. Koffel)
Richard J. Davis, FM Global, MA [I]
(Alt. to M. M. Khan)
Timothy Earl, GBH International, MI [SE]
(Alt. to M. M. Hirschler)
Sam W. Francis, American Wood Council, PA [M]
(Alt. to K. Sumathipala)
Stephen P. Fuss, U.S. Bureau of Alcohol, Tobacco, Firearms & Explosives, MD [RT]
(Alt. to D. T. Sheppard)
Richard G. Gann, National Institute of Standards & Technology, MD [RT]
(Voting Alt. to NIST Rep.)

Marc L. Janssens, Southwest Research Institute, TX [RT]
(Alt. to B. L. Badders, Jr.)
Arthur J. Parker, Hughes Associates, Inc., MD [SE]
(Alt. to J. J. Beitel)
Stanislav I. Stoliarov, University of Maryland, MD [SE]
(Alt. to A. W. Marshall)
Ineke Van Zeeland, Canadian Wood Council, Canada [M]
(Alt. to R. A. McPhee)
Robert J. Wills, American Iron and Steel Institute, AL [M]
(Alt. to F. Alfawakhiri)
Joe Ziolkowski, American Furniture Manufacturers Association, NC [M]
(Alt. to R. T. Long, Jr.)

Nonvoting

Robert H. Barker, American Fiber Manufacturers Association, VA [M]

Rohit Khanna, U.S. Consumer Product Safety Commission, MD [C]

Tracy L. Vecchiarelli, NFPA Staff Liaison

This list represents the membership at the time the Committee was balloted on the final text of this edition. Since that time, changes in the membership may have occurred. A key to classifications is found at the back of the document.

NOTE: Membership on a committee shall not in and of itself constitute an endorsement of the Association or any document developed by the committee on which the member serves.

Committee Scope: This Committee shall have primary responsibility for documents on fire testing procedures, for reviewing existing fire test standards and recommending appropriate action to NFPA, for recommending the application of and advising on the interpretation of acceptable test standards for fire problems of concern to NFPA technical committees and members, and for acting in a liaison capacity between NFPA and the committees of other organizations writing fire test standards. This Committee does not cover fire tests that are used to evaluate extinguishing agents, devices, or systems.

Contents

Chapter 1 Administration	290– 4	Chapter 6 Test Location	290– 5
1.1 Scope	290– 4	6.1 Environmental Effects	290– 5
1.2 Purpose	290– 4	6.2 Air Temperature	290– 6
1.3 Application	290– 4	6.3 Wind Limitations	290– 6
1.4 Units and Formulas	290– 4	6.4 Adverse Weather	290– 6
Chapter 2 Referenced Publications	290– 4	Chapter 7 Conduct of Tests	290– 6
2.1 General	290– 4	7.1 Test Assembly	290– 6
2.2 NFPA Publications (Reserved)	290– 4	7.2 Calibration Test	290– 6
2.3 Other Publications	290– 4	7.3 Conduct of Torch Test	290– 6
2.4 References for Extracts in Mandatory Sections (Reserved)	290– 4	7.4 Hose Stream Test	290– 6
Chapter 3 Definitions	290– 4	7.5 Conditions of Acceptance	290– 7
3.1 General	290– 4	7.6 Environmental Conditions	290– 7
3.2 NFPA Official Definitions	290– 4	7.7 Measurements	290– 7
3.3 General Definitions	290– 5	7.8 Observations	290– 7
Chapter 4 Test Specimens	290– 5	7.9 Photographs	290– 7
4.1 Construction of Test Specimen	290– 5	7.10 Video	290– 7
4.2 Construction of Rear Box	290– 5	Chapter 8 Presentation of Results	290– 7
4.3 Passive Fire Protection (PFP) Material	290– 5	8.1 Test Report	290– 7
Chapter 5 Torch Fire	290– 5	Annex A Explanatory Material	290– 7
5.1 Torch Fire Nozzle	290– 5	Annex B Informational References	290– 8
5.2 Torch Fire Exposure	290– 5	Index	290– 9
5.3 Fuel	290– 5		

NFPA 290

Standard for

Fire Testing of Passive Protection Materials for Use on LP-Gas Containers

2013 Edition

IMPORTANT NOTE: This NFPA document is made available for use subject to important notices and legal disclaimers. These notices and disclaimers appear in all publications containing this document and may be found under the heading "Important Notices and Disclaimers Concerning NFPA Documents." They can also be obtained on request from NFPA or viewed at www.nfpa.org/disclaimers.

NOTICE: An asterisk (*) following the number or letter designating a paragraph indicates that explanatory material on the paragraph can be found in Annex A.

Changes other than editorial are indicated by a vertical rule beside the paragraph, table, or figure in which the change occurred. These rules are included as an aid to the user in identifying changes from the previous edition. Where one or more complete paragraphs have been deleted, the deletion is indicated by a bullet (•) between the paragraphs that remain.

Information on referenced publications can be found in Chapter 2 and Annex B.

Chapter 1 Administration

1.1* Scope. The test described in this procedure shall be used to determine the fire resistance of passive fire protection (PFP) materials applied to the exterior of LP-Gas containers.

1.2 Purpose. This test is designed to evaluate the fire resistance of passive fire protection (PFP) materials in a torch fire environment created by the rupture of a nearby storage vessel.

1.2.1* This test procedure subjects an insulated steel plate, simulating an LP-Gas storage vessel, to a torch fire exposure for 50 minutes. After 20 minutes of the torch fire exposure, the insulated steel plate is subjected simultaneously to the torch fire exposure and a hose stream for 10 minutes.

1.3 Application.

1.3.1 This procedure shall be a test of materials and not a test of assemblies. If necessary, additional testing shall be performed to determine the effectiveness of the material protecting a particular assembly or fabrication.

1.3.2* Although the test has been designed to reproduce conditions similar to those found in fires resulting from realistic releases of hydrocarbons, this test does not guarantee a specific degree of protection from the myriad of possible fires involving LP-Gas storage vessels or containers.

1.3.3 The test involves hazardous materials and operations.

1.3.3.1 The procedure does not address all of the safety problems associated with its use.

1.3.3.2 It shall be the responsibility of the user of the procedure to establish the safety and health practices and determine the applicability of regulatory limitations before use.

1.3.3.3 It shall be the responsibility of the supplier to inform the testing laboratory of any dangerous properties of the material to be tested, fumes given off during testing, and the residues after testing.

1.3.4 Although the test specified has been designed to simulate some of the conditions that occur in an actual LP-Gas-fueled torch fire, it does not reproduce them all exactly.

1.3.4.1 The results of this test do not guarantee safety but can be used as elements of a fire hazard or fire risk assessment for structures or plants.

1.3.4.2 The fire hazard or fire risk assessment shall also take into account all the other factors that are pertinent to an assessment of the fire hazard for a particular end use.

1.3.5 This test does not offer an assessment of other properties of the passive fire protection material such as weathering, aging, shock resistance, impact or explosion resistance, flame spread, or smoke production.

1.4 Units and Formulas.

1.4.1 SI Units. Metric units of measurement in this standard are in accordance with the modernized metric system known as the International System of Units (SI).

1.4.2 Primary Values. The SI value for a measurement and the equivalent inch-pound value given in parentheses shall each be acceptable for use as primary units for satisfying the requirements of this standard.

Chapter 2 Referenced Publications

2.1 General. The documents or portions thereof listed in this chapter are referenced within this standard and shall be considered part of the requirements of this document.

2.2 NFPA Publications. (Reserved)

2.3 Other Publications.

2.3.1 ANSI/UL Publications. Underwriters Laboratories Inc., 333 Pfingsten Road, Northbrook, IL 60062-2096.

ANSI/UL 385, *Standard for Safety Play Pipes for Water Supply Testing in Fire Protection Service*, 2005, revised 2011.

2.3.2 Other Publications.

Merriam-Webster's Collegiate Dictionary, 11th edition, Merriam-Webster, Inc., Springfield, MA, 2003.

2.4 References for Extracts in Mandatory Sections. (Reserved)

Chapter 3 Definitions

3.1 General. The definitions contained in this chapter shall apply to the terms used in this standard. Where terms are not defined in this chapter or within another chapter, they shall be defined using their ordinarily accepted meanings within the context in which they are used. *Merriam-Webster's Collegiate Dictionary*, 11th edition, shall be the source for the ordinarily accepted meaning.

3.2 NFPA Official Definitions.

3.2.1 Shall. Indicates a mandatory requirement.



3.2.2 Should. Indicates a recommendation or that which is advised but not required.

3.2.3 Standard. A document, the main text of which contains only mandatory provisions using the word “shall” to indicate requirements and which is in a form generally suitable for mandatory reference by another standard or code or for adoption into law. Nonmandatory provisions are not to be considered a part of the requirements of a standard and shall be located in an appendix, annex, footnote, informational note, or other means as permitted in the *Manual of Style for NFPA Technical Committee Documents*.

3.3 General Definitions.

3.3.1 Fire Resistance. The measure of the ability of a material, product, or assembly to withstand fire or give protection from it.

3.3.2* Passive Fire Protection (PFP) Material. A material that is applied to a substrate and designed to protect it from the thermal effects of a fire.

3.3.2.1 Passive Fire Protection — Coating Material. A material that is applied to a substrate and is designed to protect it from thermal effects.

3.3.2.2 Passive Fire Protection — Panel Material. A material in the form of a panel or sheet, including pre-formed components, that is designed to stand alone prior to application to a steel substrate.

3.3.3 Rear Box. A mild steel box, open at the front and back, that is designed to be attached to the rear of the test specimen to shield it from environmental influences.

3.3.4 Torch Fire. An ignited discharge of propane vapors under pressure.

Chapter 4 Test Specimens

4.1 Construction of Test Specimen.

4.1.1 Two test specimens shall be required to conduct this test.

4.1.2 One test specimen shall be an uninsulated steel plate used for calibration of the propane torch fire exposure.

4.1.3 A second test specimen shall be a steel plate thermally protected with the insulation material at the thickness, density, and installation techniques being evaluated.

4.1.4 The test specimen dimensions shall not be less than 1.2 m × 1.2 m (4 ft × 4 ft) by nominal 16 mm (5/8 in.) thick.

4.1.5 The test specimens shall be constructed using a steel plate with thermal properties equivalent to ASME pressure vessel steel.

4.1.6 Multiple insulated test specimens shall be permitted to be evaluated in a single test program, provided the test specimens are tested consecutively.

4.1.7 The test specimen shall be mounted on a steel-plate holder such that the exposed face of the test specimen is not shielded in any way by the test specimen fixture.

4.1.8 The steel-plate holder shall be constructed in such a manner that the only heat transfer to the backside of the plate is by heat conduction through the plate and not by any other heat paths.

4.1.9 The test specimen shall be mounted vertically.

4.1.10 The rear box shall be installed to the unexposed face of the test specimen in a manner such that all joints are gastight.

4.2 Construction of Rear Box.

4.2.1 All tests require fitting the rear box to the unexposed side of the test specimen to shield the unexposed face from environmental influences.

4.2.2 The rear box shall be constructed from mild steel a minimum of 10 mm (3/8 in.) thick.

4.2.3 The rear box shall be open at the front and back and flanged at the front to allow fitting to the rear of the test specimen with no significant air gaps.

4.2.4 The internal dimensions of the rear box shall match the dimensions of the test specimen and be a minimum of 1 m (3 ft) deep.

4.3 Passive Fire Protection (PFP) Material.

4.3.1 Documentation of the method of preparation of the test specimen and the application details of the PFP material shall be provided to the test laboratory in advance of the test.

4.3.2 The test laboratory shall include this information in the test report.

Chapter 5 Torch Fire

5.1 Torch Fire Nozzle. The propane vapor shall be issued from a nozzle capable of meeting the requirements of this test standard.

5.2 Torch Fire Exposure.

5.2.1 The flame temperature from the torch fire shall be 1200°C ± 60°C (2200°F ± 140°F) for the duration of the test.

5.2.2 The velocity of the torch fire at the exposed face of the test specimen shall be 64 km/hr ± 16 km/hr (40 mph ± 10 mph) for the duration of the test.

5.2.3 The tip of the discharge nozzle shall be aimed horizontally perpendicular and centered such that the apex of the flame shall be directed to impinge on the geometric center of the test specimen.

5.2.4 The tip of the discharge nozzle shall be positioned at a distance from the exposed face of the test specimen to achieve the temperature and velocity requirements specified in 5.2.1 and 5.2.2.

5.3 Fuel.

5.3.1 The fuel shall be a propane fuel delivered as a vapor, without a liquid fraction, at a steady flow rate such that the requirements of 5.2.1 and 5.2.2 are met.

5.3.2 There shall be a means of controlling and monitoring the fuel flow of the propane fuel during the torch test.

Chapter 6 Test Location

6.1 Environmental Effects. The test shall be carried out in a test location such that environmental effects are minimized.

6.2 Air Temperature. The ambient air temperature at the start of the test shall be between -10°C and 41°C (14°F and 105°F).

6.3 Wind Limitations. The wind conditions for tests conducted outdoors shall be less than 16 km/hr (10 mph) for the duration of the test.

6.4 Adverse Weather. Tests shall not be conducted outdoors during periods of rain or fog or other adverse weather conditions that could affect the outcome of the test.

Chapter 7 Conduct of Tests

7.1 Test Assembly.

7.1.1 The test specimen shall be adequately restrained in the test specimen fixture throughout the torch and hose stream tests.

7.1.2 The test duration shall be a minimum of 50 minutes.

7.2 Calibration Test.

7.2.1 Prior to evaluating the performance of the thermal insulation system, the torch impingement shall be calibrated as described in 7.2.2 through 7.2.7.

7.2.2 An uninsulated steel plate, as described in Section 4.1, shall be installed in the steel-plate holder.

7.2.3* The unexposed face of the uninsulated steel plate shall be instrumented with not fewer than nine thermocouples.

7.2.4 The thermocouples attached to the unexposed face of the test specimen shall be divided into nine equal squares with a thermocouple affixed to the center of each square.

7.2.5 Before exposure to the torch fire, none of the thermocouple readings on the unexposed side of the steel plate shall indicate a plate temperature in excess of 38°C (100°F) or less than 0°C (32°F).

7.2.6 Temperature measurements shall be monitored during the course of the calibration test and recorded at intervals not exceeding 30 seconds.

7.2.7 A calibration test shall be deemed successful when two of the nine thermocouples record unexposed face temperatures of 427°C (800°F) within 4 minutes \pm 0.5 minute from the start of the test.

7.3 Conduct of Torch Test.

7.3.1 A thermal insulation system shall be tested in the torch environment described in Section 7.2 in the manner described in 7.3.1.1 through 7.3.1.8.

7.3.1.1 The thermal insulation system shall be applied to the exposed side of a steel plate identical to that used during the calibration test described in Section 7.2.

7.3.1.2 The unexposed side of the steel plate shall be instrumented with a minimum of nine thermocouples placed as described in 7.2.3 to record the thermal response of the steel plate.

7.3.1.3 Before exposure to the torch fire, none of the thermocouple readings on the unexposed side of the insulated steel plate shall indicate a plate temperature in excess of 38°C (100°F) or less than 0°C (32°F).

7.3.1.4 The entire surface of the thermal insulation system shall be exposed to the torch fire environment.

7.3.1.5 The test specimen shall be exposed to the torch fire environment described in Section 7.2.

7.3.1.6 The insulated test specimen shall be exposed to the torch fire for 50 minutes.

7.3.1.7 Twenty minutes into the torch test, a hose stream test shall be conducted concurrently, as described in Section 7.4, for 10 minutes.

7.3.1.8 Subsequent to the application of the hose stream, the torch test shall continue until any thermocouple on the unexposed face of the steel plate indicates a plate temperature in excess of 427°C (800°F) or until a total test time of 50 minutes has elapsed.

7.4 Hose Stream Test.

7.4.1 During the torch test, the insulated test specimen shall be exposed to a hose stream test.

7.4.2 After 20 minutes of exposure to the torch test, the test specimen shall be exposed to a hose stream test.

7.4.3 The hose stream test shall be conducted concurrently with the torch test for a period of 10 minutes.

7.4.4 The hose stream shall be delivered through a 64 mm (2 in.) diameter hose discharging through a National Standard play pipe as specified in ANSI/UL 385, *Standard for Safety Play Pipes for Water Supply Testing in Fire Protection Service*.

7.4.4.1 The play pipe shall have an overall length of 762 mm (30 in.) and shall be equipped with a 28 mm ($1\frac{1}{8}$ in.) diameter discharge tip of the standard-taper, smooth bore pattern without shoulder at the orifice.

7.4.4.2 The play pipe shall be fitted with a 64 mm (2 in.) inside diameter by 152 mm (6 in.) long nipple mounted between the hose and the base of the play pipe.

7.4.4.3 The pressure tap for measuring the water pressure at the base of the nozzle shall be normal to the surface of the nipple, centered in its length.

7.4.4.4 The pressure tap shall not protrude into the water stream.

7.4.4.5 The water pressure shall be measured with a pressure gauge [as a minimum 0 kPa to 345 kPa (0 psi to 50 psi)] graduated in no more than 13.8 kPa (2 psi) increments.

7.4.5 The gauge water pressure at the base of the nozzle and for the duration of the hose stream test shall be 207 kPa (30 psi).

7.4.5.1 The estimated delivery rate of water shall be 776 L/min (205 gpm) or 7760 L (2050 gal) over the 10-minute hose stream test.

7.4.6 Nozzle Distance. The nozzle orifice shall be located 6 m (20 ft) from and on a line normal to the center of the exposed surface of the test specimen.

7.4.6.1 If the nozzle cannot be located normal to the surface of the test specimen, the nozzle shall be on a line deviating not to exceed 30 degrees from the line normal to the center of the test specimen.

7.4.6.2 When so located, the distance from the center of the test specimen shall be less than 6 m (20 ft) by an amount equal to 0.3 m (1 ft) for each 10 degrees of deviation from the normal.



7.4.7 The hose stream shall be directed first at the middle of the test specimen and then at all parts of the exposed surface, making changes in direction slowly.

7.5 Conditions of Acceptance. None of the thermocouples on the unexposed side of the steel plate shall indicate a temperature in excess of 427°C (800°F) for a period of 50 minutes.

7.6 Environmental Conditions.

7.6.1 Environmental conditions shall be measured immediately before the test, and any significant changes during the test shall be noted.

7.6.2 The ambient temperature shall be measured. For tests conducted outdoors, wind speed and direction shall also be measured. Observations shall also be made of the weather, to indicate whether it is sunny or cloudy or whether there is any precipitation.

7.7 Measurements. A steady flow rate of propane vapor shall be required.

7.7.1 When the torch fire first impinges on the test specimen, a timer shall be started and the flow rate, temperatures, and pressures shall be monitored.

7.7.2 Readings of the instruments shall be taken at least once every 30 seconds.

7.7.3 The tests shall continue until either the time or temperature selected prior to the test is reached.

7.8 Observations.

7.8.1 Observations of significant details of the behavior and appearance of the test specimen during the test and after the torch fire is extinguished shall be recorded.

7.8.2 Information on deformation, spalling, cracking, and burning of the PFP material and continuance of flaming shall be noted.

7.9 Photographs.

7.9.1 Photographs of the test specimen shall be taken prior to and as soon as is practicable after the torch test has been extinguished.

7.9.2 The photographs described in 7.9.1 shall be included in the test report.

7.10 Video. A video record shall be made of the test.

- (b) Record of the fuel pressure and temperature at least every 30 seconds throughout the test, where these are used to calculate mass flow rate, and the method of control and calculation.
- (c) Record of fuel mass flow rate at least every 30 seconds throughout the test and total mass of fuel used.
- (d) For reacting materials, the thickness of unreacted or partially reacted material left at the end of the test and the char thickness at the positions where the initial thickness was measured. The condition of the char and the strength of bonding to the underlying material shall be recorded.
- (e) For materials restrained/supported by a reinforcing mesh, the condition of the mesh at the end of the test.
- (6) The test result, in the following format:
 - (a) The behavior and appearance of the test specimen during and after the test and photographs, as detailed in Section 7.8 and Section 7.9.
 - (b) Temperature/time plots and tables of temperatures at least every 30 seconds for each thermocouple.
 - (c) Record of the maximum temperature and the time it occurs for each thermocouple.
 - (d) Statement as to the material's performance with respect to the conditions of acceptance.

Annex A Explanatory Material

Annex A is not a part of the requirements of this NFPA document but is included for informational purposes only. This annex contains explanatory material, numbered to correspond with the applicable text paragraphs.

A.1.1 Thermal protection insulating systems are allowed for use on LP-Gas containers as a means of "Special Protection" in NFPA 58, *Liquefied Petroleum Gas Code*, and NFPA 59, *Utility LP-Gas Plant Code*. These standards have required that these materials undergo thermal performance testing as a precondition for acceptance. The intent of this testing procedure is to identify insulation systems that retard or prevent the release of the container's contents in a fire environment of 50 minutes' duration and that will resist a concurrent hose stream of 10 minutes' duration.

This test method provides a replacement for the test as described in Annex H of NFPA 58 and referenced in NFPA 59.

A.1.2.1 The torch exposure simulates the high temperature and erosive effects of a high-pressure jet of burning fuel vapor issuing from a nearby ruptured LP-Gas storage vessel. The hose stream simulates a fire fighter hose stream impingement on the insulated steel tank.

A.1.3.2 This test is an evaluation based on a "torching" type fire exposure. Other fire exposures such as a pool fire are a potential concern. It is believed, however, that the "torching" test is a worst-case fire scenario because of the high-temperature exposure coupled with the erosive effects of the high-velocity flame.

A.3.3.2 Passive Fire Protection (PFP) Material. Passive fire protection materials can be in the form of coatings or in the form of panels or sheets, including preformed components, that are designed to stand alone prior to application to a substrate.

Chapter 8 Presentation of Results

8.1 Test Report. A test report shall be produced and shall include the following information:

- (1) Name of the testing laboratory and the test date.
- (2) Names of the sponsor/customer, the manufacturer, and the product.
- (3) Documentation of how and when the test specimen was prepared, details of the application of the PFP material, and the name of the applicator company.
- (4) A description of the test specimen, including measurements of the thickness of passive fire protection material and the hardness, if measured. The mean, standard deviation, and range of measurements of thickness shall be given.
- (5) Record of test details, as follows:
 - (a) Ambient conditions.

A.7.2.3 Thermocouples can be attached to the steel plate via several methods. One such method is to weld the individual thermocouple leads directly to the steel plate, with the individual leads separated by 6 mm (¼ in.) or less. Another method is to “peen” the thermocouples in place. This entails drilling a small diameter indentation into the steel plate. This indentation is less than the diameter of the thermocouple bead. The thermocouple bead is placed in the indentation, and the surrounding metal is “peened” over the thermocouple bead to secure it in place.

Annex B Informational References

B.1 Referenced Publications. The documents or portions thereof listed in this annex are referenced within the infor-

mational sections of this standard and are not part of the requirements of this document unless also listed in Chapter 2 for other reasons.

B.1.1 NFPA Publications. National Fire Protection Association, 1 Batterymarch Park, Quincy, MA 02169-7471.

NFPA 58, *Liquefied Petroleum Gas Code*, 2011 edition.

NFPA 59, *Utility LP-Gas Plant Code*, 2012 edition.

B.1.2 Other Publications. (Reserved)

B.2 Informational References. (Reserved)

B.3 References for Extracts in Informational Sections. (Reserved)

Index

Copyright © 2013 National Fire Protection Association. All Rights Reserved.

The copyright in this index is separate and distinct from the copyright in the document that it indexes. The licensing provisions set forth for the document are not applicable to this index. This index may not be reproduced in whole or in part by any means without the express written permission of NFPA.

-A-	
Administration	Chap. 1
Application	1.3
Purpose	1.2
Scope.....	1.1, A.1.1
Units and Formulas.....	1.4
Primary Values.....	1.4.2
SI Units	1.4.1
-C-	
Conduct of Tests	Chap. 7
Calibration Test	7.2
Conditions of Acceptance.....	7.5
Conduct of Torch Test.....	7.3
Environmental Conditions.....	7.6
Hose Stream Test	7.4
Nozzle Distance	7.4.6
Measurements.....	7.7
Observations.....	7.8
Photographs.....	7.9
Test Assembly.....	7.1
Video.....	7.10
-D-	
Definitions	Chap. 3
-E-	
Explanatory Material	Annex A
-F-	
Fire Resistance	
Definition.....	3.3.1
-I-	
Informational References	Annex B
-P-	
Passive Fire Protection (PFP) Material	
Definition	3.3.2, A.3.3.2
Passive Fire Protection — Panel Material	
Definition.....	3.3.2.2
Passive Fire Protection — Coating Material	
Definition.....	3.3.2.1
Presentation of Results	Chap. 8
Test Report	8.1
-R-	
Rear Box	
Definition.....	3.3.3
Referenced Publications	Chap. 2
General	2.1
NFPA Publications (Reserved)	2.2
Other Publications.....	2.3
References for Extracts in Mandatory Sections (Reserved)	2.4
-S-	
Shall	
Definition.....	3.2.1
Should	
Definition.....	3.2.2
Standard	
Definition.....	3.2.3
-T-	
Test Location	Chap. 6
Adverse Weather	6.4
Air Temperature	6.2
Environmental Effects.....	6.1
Wind Limitations.....	6.3
Test Specimens	Chap. 4
Construction of Rear Box	4.2
Construction of Test Specimen	4.1
Passive Fire Protection (PFP) Material.....	4.3
Torch Fire	
Definition.....	3.3.4
Torch Fire	Chap. 5
Fuel.....	5.3
Torch Fire Exposure.....	5.2
Torch Fire Nozzle.....	5.1

Sequence of Events Leading to Issuance of This NFPA Committee Document

Step 1: Call for Proposals

- Proposed new Document or new edition of an existing Document is entered into one of two yearly revision cycles, and a Call for Proposals is published.

Step 2: Report on Proposals (ROP)

- Committee meets to act on Proposals, to develop its own Proposals, and to prepare its Report.
- Committee votes by written ballot on Proposals. If two-thirds approve, Report goes forward. Lacking two-thirds approval, Report returns to Committee.
- Report on Proposals (ROP) is published for public review and comment.

Step 3: Report on Comments (ROC)

- Committee meets to act on Public Comments to develop its own Comments, and to prepare its report.
- Committee votes by written ballot on Comments. If two-thirds approve, Report goes forward. Lacking two-thirds approval, Report returns to Committee.
- Report on Comments (ROC) is published for public review.

Step 4: Technical Report Session

- “*Notices of intent to make a motion*” are filed, are reviewed, and valid motions are certified for presentation at the Technical Report Session. (“Consent Documents” that have no certified motions bypass the Technical Report Session and proceed to the Standards Council for issuance.)
- NFPA membership meets each June at the Annual Meeting Technical Report Session and acts on Technical Committee Reports (ROP and ROC) for Documents with “certified amending motions.”
- Committee(s) vote on any amendments to Report approved at NFPA Annual Membership Meeting.

Step 5: Standards Council Issuance

- Notification of intent to file an appeal to the Standards Council on Association action must be filed within 20 days of the NFPA Annual Membership Meeting.
- Standards Council decides, based on all evidence, whether or not to issue Document or to take other action, including hearing any appeals.

Committee Membership Classifications

The following classifications apply to Technical Committee members and represent their principal interest in the activity of the committee.

- M *Manufacturer*: A representative of a maker or marketer of a product, assembly, or system, or portion thereof, that is affected by the standard.
- U *User*: A representative of an entity that is subject to the provisions of the standard or that voluntarily uses the standard.
- I/M *Installer/Maintainer*: A representative of an entity that is in the business of installing or maintaining a product, assembly, or system affected by the standard.
- L *Labor*: A labor representative or employee concerned with safety in the workplace.
- R/T *Applied Research/Testing Laboratory*: A representative of an independent testing laboratory or independent applied research organization that promulgates and/or enforces standards.
- E *Enforcing Authority*: A representative of an agency or an organization that promulgates and/or enforces standards.
- I *Insurance*: A representative of an insurance company, broker, agent, bureau, or inspection agency.
- C *Consumer*: A person who is, or represents, the ultimate purchaser of a product, system, or service affected by the standard, but who is not included in the *User* classification.
- SE *Special Expert*: A person not representing any of the previous classifications, but who has a special expertise in the scope of the standard or portion thereof.

NOTES:

1. “Standard” connotes code, standard, recommended practice, or guide.
2. A representative includes an employee.
3. While these classifications will be used by the Standards Council to achieve a balance for Technical Committees, the Standards Council may determine that new classifications of members or unique interests need representation in order to foster the best possible committee deliberations on any project. In this connection, the Standards Council may make appointments as it deems appropriate in the public interest, such as the classification of “Utilities” in the National Electrical Code Committee.
4. Representatives of subsidiaries of any group are generally considered to have the same classification as the parent organization.

Submitting Public Input / Public Comment through the Electronic Submission System (e-Submission):

As soon as the current edition is published, a Standard is open for Public Input.

Before accessing the e-Submission System, you must first sign-in at www.NFPA.org. *Note: You will be asked to sign-in or create a free online account with NFPA before using this system:*

- a. Click in the gray Sign In box on the upper left side of the page. Once signed-in, you will see a red “Welcome” message in the top right corner.
- b. Under the Codes and Standards heading, Click on the Document Information pages (List of Codes & Standards), and then select your document from the list or use one of the search features in the upper right gray box.

OR

- a. Go directly to your specific document page by typing the convenient short link of www.nfpa.org/document#, (Example: NFPA 921 would be www.nfpa.org/921) Click in the gray Sign In box on the upper left side of the page. Once signed in, you will see a red “Welcome” message in the top right corner.

To begin your Public Input, select the link The next edition of this standard is now open for Public Input (formally “proposals”) located on the Document Information tab, the Next Edition tab, or the right-hand Navigation bar. Alternatively, the Next Edition tab includes a link to Submit Public Input online

At this point, the NFPA Standards Development Site will open showing details for the document you have selected. This “Document Home” page site includes an explanatory introduction, information on the current document phase and closing date, a left-hand navigation panel that includes useful links, a document Table of Contents, and icons at the top you can click for Help when using the site. The Help icons and navigation panel will be visible except when you are actually in the process of creating a Public Input.

Once the First Draft Report becomes available there is a Public comment period during which anyone may submit a Public Comment on the First Draft. Any objections or further related changes to the content of the First Draft must be submitted at the Comment stage.

To submit a Public Comment you may access the e-Submission System utilizing the same steps as previous explained for the submission of Public Input.

For further information on submitting public input and public comments, go to: <http://www.nfpa.org/publicinput>

Other Resources available on the Doc Info Pages

Document information tab: Research current and previous edition information on a Standard

Next edition tab: Follow the committee’s progress in the processing of a Standard in its next revision cycle.

Technical committee tab: View current committee member rosters or apply to a committee

Technical questions tab: For members and Public Sector Officials/AHJs to submit questions about codes and standards to NFPA staff. Our Technical Questions Service provides a convenient way to receive timely and consistent technical assistance when you need to know more about NFPA codes and standards relevant to your work. Responses are provided by NFPA staff on an informal basis.

Products/training tab: List of NFPA’s publications and training available for purchase.

Community tab: Information and discussions about a Standard