

# AEROSPACE MATERIAL SPECIFICATION

SAE,

**AMS 1526B** 

Issued Revised Reaffirmed JUL 1977 APR 1990 JUN 2000

Superseding AMS 1526A

Cleaner for Aircraft Exterior Surfaces Water-Miscible, Pressure-Spraying Type

1. SCOPE:

1.1 Form:

This specification covers a water-miscible, low-foaming cleaner in the form of a liquid.

1.2 Application:

Primarily for removing soils from painted and unpainted exterior surfaces of aircraft by pressure spray or manual application.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

FAX: (724) 776-0243

FAX: (724) 776-0790

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

## 2.1.1 Aerospace Material Specifications:

AMS-2470	Anodic Treatment of Aluminum Alloys, Chromic Acid Process
AMS-2475	Protective Treatments, Magnesium Alloys
AMS-2825	Material Safety Data Sheets
AMS-4037	Aluminum Alloy Sheet and Plate, 4.4Cu - 1.5Mg - 0.60Mn (2024; -T3 Flat Sheet,
	-T351 Plate), Solution Heat Treated
AMS-4041	Aluminum Alloy Sheet and Plate, Alclad, 4.4Cu - 1.5Mg - 0.60Mn (Alclad 2024 and
	1-1/2% Alclad 2024-T3 Flat Sheet; 1-1/2% Alclad 2024-T351 Plate)
AMS-4049	Aluminum Alloy Sheet and Plate, Alclad, 5.6Zn - 2.5Mg - 1.6Cy 0.23Cr (Alclad
	7075; -T6 Sheet, -T651 Plate), Solution and Precipitation Heat Treated
AMS-4376	Magnesium Alloy Plate, 3.0Al - 1.0Zn (AZ31B-H26), Cold Rolled and Partially
	Annealed
AMS-4911	Titanium Alloy Sheet, Strip, and Plate, 6AI - 4V, Annealed
AMS-5045	Steel Sheet and Strip, 0.25 max Carbon, Hard Temper

## 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM D 56	Flash Point by Tag Closed Tester
ASTM D 1193	Reagent Water
ASTM D 1568	Sampling and Chemical Analysis of Alkylbenzene Sulfonates
ASTM F 483	Total Immersion Corrosion Test for Aircraft Maintenance Chemicals
ASTM F 484	Stress Crazing of Acrylic Plastics in Contact with Liquid or Semi-Liquid Compounds
ASTM F 485	Effects of Cleaners on Unpainted Aircraft Surfaces
ASTM F 502	Effects of Cleaning and Chemical Maintenance Materials on Painted Aircraft
	Surfaces
ASTM F 519	Mechanical Hydrogen Embrittlement Testing of Plating Processes and Aircraft
	Maintenance Chemicals
ASTM F 1105	Preparing Aircraft Cleaning Compounds, Liquid Type, Solvent Based for Storage
	Stability Testing
ASTM F 1110 /	Sandwich Corrosion Test
ASTM F 1111	Corrosion of Low Embrittling Cadmium Plate by Aircraft Maintenance Chemicals

## 2.3 U. S. Government Publications:

Available from Naval Publications and Forms Center, Attn: NPODS, 5801 Tabor Avenue, Philadelphia, PA 19120-5099.

## 2.3.1 Military Specifications:

MIL-P-25690 Plastic, Sheets and Parts, Modified Acrylic Base, Monolithic, Crack Propagation Resistant

SAE	AMS 1526B
	SAE

## 2.3.2 Military Standards:

MIL-STD-794 Parts and Equipment, Procedures for Packaging and Packing of

### 3. TECHNICAL REQUIREMENTS:

#### 3.1 Material:

The composition of the cleaner shall be optional with the manufacturer but should contain water, biodegradable surfactants and/or soap builders, emulsifiers, and solvents to produce a low-foaming product completely miscible in water and meeting the requirements of 3.2.

## 3.2 Properties:

The cleaner shall conform to the following requirements; tests shall be performed in accordance with specified test methods on the product supplied in concentrated form and at use dilution recommended by the manufacturer; diluent shall be ASTM D 1193, Type IV, water.

## 3.2.1 Corrosion of Metal Surfaces:

- 3.2.1.1 Sandwich Corrosion: Specimens, after test, shall show a rating not worse than 1, determined in accordance with ASTM F 1110.
- 3.2.1.2 Total Immersion Corrosion: The product shall neither show evidence of corrosion of the panels nor cause a weight change of any test panel greater than the following, determined in accordance with ASTM F 483:

Panel	Weight Change mg/cm <sup>2</sup> per 24 hours
AMS-4037 Aluminum Alloy, anodized as in AMS-2470	0.3
AMS-4041 Aluminum Alloy (optional)	0.3
AMS-4049 Aluminum Alloy	0.3
AMS-4376 Magnesium Alloy, dichromate treated as in AMS-2475	0.2
AMS-4911 Titanium Alloy	0.1
AMS-5045 Carbon Steel	0.8

3.2.1.3 Low-Embrittling Cadmium Plate: Panels coated with low-embrittling cadmium plate shall not show a weight change greater than 0.3 mg/cm<sup>2</sup> per 24 hours, determined in accordance with ASTM F 1111.

- 3.2.2 Hydrogen Embrittlement: The product shall be non-embrittling, determined in accordance with ASTM F 519, Type 1a, 1c, or 2a.
- 3.2.3 Flash Point: Shall be not lower than 60 °C (140 °F), determined in accordance with ASTM D 56.
- 3.2.4 Effect on Transparent Acrylic Plastics: There shall be no crazing or staining of stretched MIL-P-25690 plastic, determined in accordance with ASTM F 484.
- 3.2.5 Effect on Painted Surfaces: The product shall neither decrease the hardness of the paint film by more than two pencil hardness levels nor shall it produce any streaking, discoloration, or blistering of the paint film, determined in accordance with ASTM F 502.
- 3.2.6 Effect on Unpainted Surfaces: The product, tested in accordance with ASTM F 485, shall neither produce streaking nor leave any stains requiring polishing to remove.
- 3.2.7 Storage Stability: The product shall neither show separation from exposure to heat or cold nor show an increase in turbidity greater than a control sample equally diluted to use concentration with ASTM D 1193, Type IV, water, determined in accordance with ASTM F 1105.
- 3.2.8 Performance: The product, used in accordance with manufacturer's recommendations, shall remove normally accumulated soils from exterior surfaces of aircraft. No visible residue shall remain on any surface tested. Standards for acceptance shall be as agreed upon by purchaser and vendor.

#### 3.3 Quality:

The cleaner, as received by purchaser, shall be homogeneous, uniform in color, and free from skins and lumps and from foreign materials detrimental to usage of the cleaner.

#### 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the cleaner shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the cleaner conforms to the requirements of this specification.

- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests for effect on transparent acrylic plastics (3.2.4), effect on unpainted surfaces (3.2.6), and quality (3.3) are acceptance tests and shall be performed on each lot.
- 4.2.2 Periodic Tests: Tests for corrosion of metal surfaces (3.2.1), hydrogen embrittlement (3.2.2), flash point (3.2.3), effect on painted surfaces (3.2.5), storage stability (3.2.7), and performance (3.2.8) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

- 4.2.3 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of cleaner to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.
- 4.3 Sampling and Testing:

Shall be in accordance with ASTM D 1568; a lot shall be all cleaner produced in a single production run from the same batches of raw materials under the same fixed conditions and presented for vendor's inspection at one time.

- 4.4 Approval:
- 4.4.1 Sample cleaner shall be approved by purchaser before cleaner for production use is supplied, unless such approval be waived by purchaser. Results of tests on production cleaner shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, and methods of inspection on production cleaner which are essentially the same as those used on the approved sample cleaner. If necessary to make any change in ingredients or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample cleaner. Production cleaner made by the revised procedure shall not be shipped prior to receipt of reapproval.
- 4.5 Reports:

The vendor of cleaner shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and, when performed, to the periodic test requirements and stating that the cleaner conforms to the other technical requirements. This report shall include the purchase order number, AMS-1526B, manufacturer's identification, lot number, and quantity.

4.5.1 A material safety data sheet conforming to AMS-2825, or equivalent, shall be supplied to each purchaser prior to, or concurrent with, the report of preproduction test results or, if preproduction testing be waived by purchaser, concurrent with the first shipment of cleaner for production use. Each request for modification of cleaner formulation shall be accompanied by a revised data sheet for the proposed formulation.