



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 2481D

Superseding AMS 2481C

Issued 5-1-48
Revised 7-16-79

PHOSPHATE TREATMENT Anti-Chafing

1. SCOPE:

1.1 Purpose: This specification covers the engineering requirements for producing a phosphate coating on ferrous alloys and the properties of the coating.

1.2 Application: Primarily to produce a coating which will minimize chafing of contacting steel surfaces and effectively retain an oil film.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

2.2 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Preparation:

3.1.1 All heat treatment, machining, forming, brazing, welding, and perforating operations shall, \emptyset insofar as practicable, be completed before parts are treated.

3.1.2 Parts, prior to being treated, shall have chemically clean surfaces, free from waterbreaks, \emptyset prepared with minimum abrasion, erosion, or pitting.

3.2 Procedure: Parts shall be coated by immersing in a balanced manganese acid phosphate solution containing a suitable accelerating agent for sufficient time to produce the desired coating. Solution shall be maintained at 190° - 210° F (90° - 100° C). Immediately after processing, parts shall be rinsed thoroughly in cold running water.

3.3 Post Treatment: After the cold water rinse, parts shall be dipped in hot water. The hot water rinse may contain small amounts of chromic acid or chromic and phosphoric acids. Parts shall be thoroughly dried unless a water-displacing oil is used for protection of parts in which case, drying may be omitted. Dried parts shall be oiled with a suitable corrosion-inhibiting oil.

SAE Technical and rules provide that: "All technical reports, including standards approved and prepared by SAE, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

3.4 Color: Coated parts shall have a uniform, usually grayish-black, finely-crystalline appearance.

3.5 Quality: Surfaces of treated parts shall be uniform in texture and appearance. Powdery areas, \emptyset excessive buildup, and darkening of corners and edges are not acceptable.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The processing vendor shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the \emptyset purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that processing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the initial shipment of coated parts to a purchaser, when a change in material or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, \emptyset the contracting officer, or the request for procurement.

4.3 Sampling: Shall be as agreed upon by purchaser and vendor; a lot shall be all parts processed in \emptyset the same solution in not longer than 8 hr of continuous operation and presented for vendor's inspection at one time.

4.4 Approval:

4.4.1 Sample coated parts shall be approved by purchaser before parts for production use are supplied, unless such approval be waived. Results of tests on production parts shall be essentially equivalent to those on the approved samples.

4.4.2 Vendor shall use manufacturing procedures, processes, and methods of inspection on production parts which are essentially the same as those used on the approved sample parts. If any change is necessary in type of equipment or in established composition limits and operating conditions \emptyset of process solutions, vendor shall submit for reapproval of the process a statement of the proposed changes in processing and, when requested, sample coated parts. Production parts coated by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports: The vendor of coated parts shall furnish with each shipment three copies of a report stating that the parts have been processed and tested in accordance with the requirements of this \emptyset specification and that the parts conform to the technical requirements. This report shall include the purchase order number, this specification number and its revision letter, part number, and quantity.

4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the parts may be based on the results of testing three additional \emptyset specimens for each original nonconforming specimen. Except as specified in 4.6.1, failure of any retest specimen to meet the specified requirements shall be cause for rejection of the parts represented and no additional testing shall be permitted. Results of all tests shall be reported.

4.6.1 If any part fails to meet the specified requirements, either on the original sampling as in 4.3 \emptyset or upon resampling as in 4.6, the parts in that lot may be stripped by a method approved by purchaser which does not roughen, pit, or embrittle the basis metal, recoated, and retested.