



AEROSPACE MATERIAL SPECIFICATION



AMS 2675G

Issued NOV 1952
Revised APR 2002
Reaffirmed SEP 2006

Superseding AMS 2675F

Brazing, Nickel Alloy Filler Metal

RATIONALE

This document has been reaffirmed to comply with the SAE 5-year Review policy.

1. SCOPE:

1.1 Purpose:

This specification covers the engineering requirements for producing brazed joints in parts made of steels, iron alloys, nickel alloys, and cobalt alloys by use of nickel alloy filler metal.

1.2 Application:

This process has been used typically for joints requiring high strength and corrosion and oxidation resistance up to 1200 °F (649 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International
All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org

SAE WEB ADDRESS: <http://www.sae.org>

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2403 Plating, Nickel, General Purpose

AMS 2424 Plating, Nickel, Low-Stressed Deposit

AMS 2750 Pyrometry

AMS 4775 Nickel Alloy, Brazing Filler Metal, 73Ni - 0.75C - 4.5Si - 14Cr - 3.1B - 4.5Fe, 1790 to 1970 °F (977 to 1077 °C) Solidus-Liquidus Range

2.2 ASME Publications:

Available from ASME, Order/Inquiries, P.O. Box 2300, Fairfield, NJ 07007-2300 or www.asme.org.

ASME B46.1 Surface Texture, Surface Roughness, Waviness and Lay

3. TECHNICAL REQUIREMENTS:**3.1 Materials:**

3.1.1 Filler Metal: Shall conform to AMS 4775, unless otherwise specified. (See 8.2).

3.1.2 Flux: Paste or liquid fluxes shall not be used, unless agreed upon by purchaser.

3.2 Equipment:

Furnaces, with suitable protective atmospheres as defined in 3.3, shall be used for brazing unless electrical induction, electrical resistance heating, or other method is permitted by purchaser. Where brazing is concurrent with heat treatment, the pyrometry requirements of the applicable heat treatment specification shall be applied. Otherwise, pyrometry shall be in accordance with AMS 2750.

3.3 Atmospheres:

Acceptable furnace atmosphere for brazing shall be as follows:

3.3.1 Hydrogen of not less than 99.99% purity and dew point not higher than -25 °F (-32 °C).

3.3.2 Argon of not less than 99.99% purity and dew point not higher than -35 °F (-37 °C).

3.3.3 Mixtures of argon and hydrogen in any proportions, the hydrogen purity being as specified in 3.3.1, the argon purity being as specified in 3.3.2, and the dew point of the mixture being not higher than -35 °F (-37 °C).

3.3.4 Vacuum of 5×10^{-3} Torr or better (lower pressure). Back-fill to a higher pressure may be achieved with a non-oxidizing atmosphere (See 3.3.2 or 3.3.3).

3.4 Preparation:

3.4.1 Surface Condition: The surfaces to be joined shall be clean prior to assembly (See 8.5).

3.4.2 Nickel Plating: Unless otherwise specified, joints shall be prepared as noted in Table 1 by nickel plating in accordance with AMS 2403 or AMS 2424.

TABLE 1 - Nickel Plating Thickness Requirements for Furnace Atmosphere

Alloy	Nickel Plating Thickness Inch (μm) Vacuum	Nickel Plating Thickness Inch (μm) Non-Oxidizing Gas
Precipitation Hardenable Iron Alloys	0.0001 to 0.0006 (2.5 to 15)	0.0004 to 0.0006 (10 to 15)
Precipitation Hardenable Nickel Alloys		
(a) Ti + Al content under 4% nominal	0.0001 to 0.0006 (2.5 to 15)	0.0004 to 0.0006 (10 to 15)
(b) Ti + Al content 4% nominal or greater	0.0001 to 0.0006 (2.5 to 15)	0.0008 to 0.0012 (20 to 30)
Non-precipitation Hardenable Nickel Alloys with Ti + Al content under 1% nominal	Optional to 0.0006 (15), max	0.0001 to 0.0006 (2.5 to 15)
All other Alloys	Optional to 0.0006 (15), max	Optional to 0.0006 (15), max

3.4.2.1 Unless otherwise specified, nickel plating on areas other than the faying surface and adjacent fillet is optional and may be incomplete.

3.4.3 Assembly: The parts to be joined shall be assembled so that the clearances between mating surfaces are within specified tolerances. When joint tolerances are not specified, the joint clearance shall be 0.001 to 0.004 inch (25 to 102 μm), (See 8.2). When permitted by purchaser, tack welding may be used to facilitate assembly. The assembly shall be supported so that the parts will be in proper alignment throughout the brazing process. Sufficient filler metal shall be placed at one end of the joint. In the case of blind joints, the filler metal shall be preplaced at the blind end of the joint.

3.4.4 Fluxing: When use of paste or liquid flux is permitted, flux shall be applied to the joint areas of parts. Gaseous hydrogen fluoride pre-cleaning/fluxing may be performed, when permitted by purchaser.

3.5 Procedure:

3.5.1 Joining: Parts shall be heated in equipment as in 3.2 using an atmosphere as in 3.3 and held at temperature until the filler metal melts and the joint is formed. The brazing temperature shall be from 25 to 200 F (14 to 111 C) degrees above the liquidus for the filler metal used. After the filler metal melts, heating may be prolonged to aid diffusion.

3.5.2 Cooling: After brazing, assemblies shall be cooled in a manner and at a rate that will prevent cracks and minimize internal stress, distortion, scaling, and decarburization. Cooling from the brazing temperature to below the scaling temperature shall be performed in one of the atmospheres described in 3.3. If heat treating (hardening) is to be executed in conjunction with brazing, cooling procedures may be revised accordingly.

3.6 Post Treatment:

3.6.1 Flux Removal: After brazing and cooling, the residues of paste or liquid fluxes, if used, shall be removed from the parts by a method not injurious to the specified surface finish.

3.6.2 Heat Treatment: Where heat treatment is required and the heat treatment temperature is below 1780 °F (971 °C), such heat treatment shall follow the brazing operations or, when acceptable to purchaser, may be performed during the post-braze cool down process.

3.7 Properties:

Brazed parts shall conform to the following requirements:

3.7.1 Appearance: Examination of visible joint edges shall show a complete line or ring of filler metal between component parts.

3.7.2 Coverage: The area joined by filler metal shall not be less than 80% of the area of the mating portions of the assembly, determined by a method acceptable to purchaser.

3.7.3 Proof Test: When specified, any part from a lot shall pass a proof test determined by a method acceptable to purchaser.

3.8 Quality:

Brazed joints shall be sound, clean, and free from foreign materials and from imperfections detrimental to performance of the brazed joints.

3.8.1 Surfaces of parts shall be free from excessive filler metal that interferes with form, fit, or function.

3.8.2 The presence of unmelted filler metal is not acceptable.

3.8.3 Erosion of the base metal shall not exceed 20% of the thinnest member or 0.002 inch (51 µm), whichever is less.

3.8.4 Unless otherwise specified, the depth of diffusion of solid substitution alloying elements (i.e., chromium, nickel, cobalt, tungsten, etc) at the joint shall not exceed 0.004 inch (102 µm), measured from the original base metal surface.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The brazing facility shall supply all samples for processor's tests and shall be responsible for performance of all required tests. Where actual or simulated parts are required for processor's tests, such parts shall be supplied by purchaser. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that processing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for all technical requirements with the exception of braze coverage (3.7.2) and depth of diffusion (3.8.4) are acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Destructive examination for braze coverage (3.7.2) and depth of diffusion (3.8.4) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: All technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of brazed parts to a purchaser, when any change in material and/or processing requires approval by the cognizant engineering organization (See 4.4.2), and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing:

Shall be not less than the following; a lot shall be all assemblies of the same part number brazed in the same equipment without breakdown of setup and presented for processor's inspection at one time:

4.3.1 For Acceptance Tests: Shall be as shown in Table 2.

TABLE 2 - Sampling for Acceptance Tests

Number of Parts in Lot	Quality and Appearance	Coverage
Up to 7	All	3
8 to 15	7	4
16 to 40	10	4
41 to 110	15	5
111 to 300	25	6
301 to 500	35	7
Over 500	50	8