



400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

AMS 4008G

Issued 11-1-41
Revised 4-1-89

Superseding AMS 4008F

Submitted for recognition as an American National Standard

ALUMINUM ALLOY SHEET AND PLATE
1.25Mn - 0.12Cu (3003-H14)
Strain Hardened

UNS A93003

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of sheet and plate.

1.2 Application: Primarily for parts requiring moderately severe forming or spinning.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2202 - Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate
MAM 2202 - Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate

AMS 2350 - Standards and Test Methods

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings

MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from ASTM, 1915 Race Street, Philadelphia, PA 19103.

ASTM B660 - Packaging/Packing of Aluminum and Magnesium Products

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

	min	max
Manganese	1.0	1.5
Copper	0.05	0.20
Iron	--	0.7
Silicon	--	0.6
Zinc	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum		remainder

3.2 Condition: Strain hardened.

3.3 Properties: The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as specified in Table I and 3.3.1.1.
Ø

TABLE I

Nominal Thickness Inches	Tensile Strength psi	Yield Strength at 0.2% Offset psi, min	Elongation in 2 Inches or 4D , minimum
0.009 to 0.012, incl	20,000 - 26,000	17,000	1
Over 0.012 to 0.019, incl	20,000 - 26,000	17,000	2
Over 0.019 to 0.031, incl	20,000 - 26,000	17,000	3
Over 0.031 to 0.050, incl	20,000 - 26,000	17,000	4
Over 0.050 to 0.113, incl	20,000 - 26,000	17,000	5
Over 0.113 to 0.161, incl	20,000 - 26,000	17,000	6
Over 0.161 to 0.249, incl	20,000 - 26,000	17,000	7
Over 0.249 to 0.499, incl	20,000 - 26,000	17,000	8
Over 0.499 to 1.000, incl	20,000 - 26,000	17,000	10

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm or 4D %, minimum
0.23 to 0.30, incl	138 - 179	117	1
Over 0.30 to 0.48, incl	138 - 179	117	2
Over 0.48 to 0.79, incl	138 - 179	117	3
Over 0.79 to 1.27, incl	138 - 179	117	4
Over 1.27 to 2.87, incl	138 - 179	117	5
Over 2.87 to 4.09, incl	138 - 179	117	6
Over 4.09 to 6.32, incl	138 - 179	117	7
Over 6.32 to 12.67, incl	138 - 179	117	8
Over 12.67 to 25.40, incl	138 - 179	117	10

3.3.1.1 Tensile properties of plate over 1.000 inch (25.40 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.2 Bending: Product 0.249 inch (6.32 mm) and under in nominal thickness shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

Nominal Thickness		Bend Factor
Inch	Millimetres	
0.009 to 0.113, incl	0.23 to 2.87, incl	0
Over 0.113 to 0.249, incl	Over 2.87 to 6.32, incl	2

3.3.2.1 Bending requirements for plate over 0.249 inch (6.32 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances: Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for bending (3.3.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment a report stating that the product conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS 4008G, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4008G, contractor or other direct supplier of product, part number, and quantity. When product for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of product to determine conformance to the requirements of this specification and shall include in the report either a statement that the product conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet and plate shall be marked on one face, in the respective location indicated below, with the alloy number and temper, AMS 4008 or applicable Federal specification designation, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the product or its performance.

5.1.1 Flat Sheet and Plate Under 6 Inches (152 mm) Wide: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).