

AEROSPACE MATERIAL SPECIFICATION

SAE AMS4150

REV. M

Issued 1944-03
Reaffirmed 2008-05
Revised 2013-04

Superseding AMS4150L

Aluminum Alloy, Extrusions and Rings
1.0Mg - 0.60Si - 0.28Cu - 0.20Cr - (6061-T6)
Solution and Precipitation Heat Treated
(Composition similar to UNS A96061)

RATIONALE

AMS4150M has been revised to add billet types for tubing (1.1.1) to permit the replacement of AMS-QQ-A-200/8 Temper T6 material, provides for press solution heat treatment (3.2.2), adds provisions for ultrasonic inspection, when specified (3.4.1), and revises Classification of Tests (4.2), Sampling and Testing (4.3.1) and Reports (4.4).

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of extruded bars, rods, wire, profiles, and tubing, flash welded rings fabricated from extruded stock, and stock for flash welded rings.

1.1.1 Tubing

Tubing shall be additionally classified as follows:

Type	Description
I -	Seamless tubing extruded from hollow billets using die and mandrel
II -	Tubing extruded from solid billets using porthole or spider die or similar tooling

When no Type is specified, Type I shall apply.

1.2 Application

These products have been used typically for parts requiring moderate strength, especially where such parts require brazing or welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent supplied herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4150M>**

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2355	Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings
AMS2772	Heat Treatment of Aluminum Alloy Raw Materials
AMS7488	Rings, Flash Welded, Aluminum and Aluminum Alloys
AS1990	Aluminum Alloy Tempers

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B 594	Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications
ASTM B 660	Packaging/Packing of Aluminum and Magnesium Products
ASTM B 666/B 666M	Identification Marking of Aluminum and Magnesium Products
ASTM B 807/B 807M	Extrusion Press Solution Heat Treatment for Aluminum Alloys

2.3 ANSI Publications

Available from American National Standards Institute, 25 West 43rd Street, New York, NY 10036-8002, Tel: 212-642-4900, www.ansi.org.

ANSI H35.2	Dimensional Tolerances for Aluminum Mill Products
ANSI H35.2M	Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

TABLE 1 - COMPOSITION

Element	min	max
Silicon	0.40	0.8
Iron	--	0.7
Copper	0.15	0.40
Manganese	--	0.15
Magnesium	0.8	1.2
Chromium	0.04	0.35
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminium	remainder	

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Bars, Rods, Wire, Shapes, and Tubing

Extruded and solution and precipitation heat treated to the T6 temper (See AS1990).

3.2.2 Extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within specified dimensional tolerances.

3.2.3 Heat Treatment shall be classified as follows:

Class	Description
1	Furnace solution heat treated in accordance with AMS2772 and precipitation heat treated in accordance with AMS2772.
2	Extruded and press solution heat treated in accordance with ASTM B807/B807M and precipitation heat treated in accordance with AMS2772.

If no Class is specified, either Class may be provided.

3.2.4 Flash Welded Rings

Manufactured in accordance with AMS7488 from extruded stock and solution and precipitation heat treated to the T6 temper in accordance with AMS2772.

3.2.5 Stock for Flash Welded Rings

As ordered by the flash welded ring manufacturer.

3.3 Properties

The product shall conform to the following requirements, determined on the mill produced size in accordance with AMS2355 (See 8.2).

3.3.1 Bars, Rods, Wire, Profiles, Tubing, and Flash Welded Rings

3.3.1.1 Tensile Properties

Shall be as shown in Table 2.

TABLE 2A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Diameter or Least Thickness (See 8.3) (bars, rods, wire, shapes, and flash welded rings) or Nominal Wall Thickness (tubing) Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.250, excl	38.0	35.0	8
0.250 and over	38.0	35.0	10

TABLE 2B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Diameter or Least Thickness (See 8.3) (bars, rods, wire, shapes, and flash welded rings) or Nominal Wall Thickness (tubing) Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 6.35, excl	262	241	8
6.35 and over	262	241	10

3.3.2 Stock for Flash Welded Rings

Specimens taken from the stock after solution and precipitation heat treatment in accordance with AMS2772 shall conform to the requirements of 3.3.1.1.

3.4 Quality

Extrusions, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the extrusions.

3.4.1 When specified, extrusions shall be subjected to ultrasonic inspection in accordance with ASTM B 594. Extrusions, 0.50 inch (12.7 mm) and over in nominal diameters or least distance between parallel sides, not exceeding 600 pounds (272 kg) per piece, or a 10 to 1 width-to-thickness ratio, shall meet ultrasonic Class B.

3.5 Tolerances

Bars, rods, wire, profiles, and tubing shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

Composition (3.1), tensile properties (3.3.1.1), ultrasonic inspection when specified (3.4.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each inspection lot.

4.3 Sampling and Testing

Shall be in accordance with AMS2355.

4.3.1 Additional Sampling and Testing of Material Press Solution Heat Treated

Compliance with the requirements of Table 2 shall be determined by hardness tests followed by tension tests performed on samples from the two softest extrusions in the inspection lot. The method of hardness testing shall be left to the discretion of the producer.