

AEROSPACE MATERIAL SPECIFICATIONS

AMS 5547B

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N.Y. 10017

Issued 9-15-57
Revised 9-1-65

STEEL SHEET AND STRIP, CORROSION AND MODERATE HEAT RESISTANT 15.5Cr - 4.5Ni - 2.9Mo - 0.10N Solution Heat Treated

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for parts and assemblies requiring high strength and oxidation resistance up to 800 F (427 C) and where parts require welding during fabrication.
3. **COMPOSITION:**

	min		max
Carbon	0.10	-	0.15
Manganese	0.50	-	1.25
Silicon	--		0.50
Phosphorus	--		0.040
Sulfur	--		0.030
Chromium	15.00	-	16.00
Nickel	4.00		5.00
Molybdenum	2.50	-	3.25
Nitrogen	0.07	-	0.13

Ø 3.1 **Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2248.

4. **CONDITION:**

- Ø 4.1 **Sheet:** Hot or cold rolled, solution heat treated, and descaled (No. 2D Finish or equivalent).
- Ø 4.2 **Strip:** Cold rolled, solution heat treated, and descaled (No. 1 Strip Finish).

5. **TECHNICAL REQUIREMENTS:**

- 5.1 **Heat Treatment:** Unless otherwise specified, material shall be solution heat treated by heating to 1900 F \pm 25 (1037.8 C \pm 14), holding at heat for not less than 45 min. per inch of thickness, and quenching in water or otherwise cooling as rapidly as possible to room temperature.
- 5.2 **Hardness:** Shall be not higher than Rockwell C 35 or equivalent.
- 5.3 **Bending:** Material shall withstand, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to three times the nominal thickness, with axis of bend parallel to direction of rolling.
- 5.4 **Properties After Heat Treatment:** Material shall conform to the following requirements when heat treated as follows: Re-solution heat treat by heating to 1900 F \pm 25 (1037.8 C \pm 14), holding at heat for not less than 45 min. per inch of thickness, and quenching in water or otherwise cooling as rapidly as possible to room temperature; cool to not higher than -100 F (-73 C), hold at this temperature for not less than 3 hr, and warm in air to room temperature; austenite condition by heating to 1750 F \pm 10 (954.4 C \pm 5.6), holding at heat for not less than 10 min. but not more than 1 hr, and quenching in water or otherwise cooling as rapidly as possible to room temperature; cool to not higher than -100 F (-73 C), hold at this temperature for not less than 3 hr, and warm in air to room temperature; temper by heating to 1000 F \pm 25 (537.8 C \pm 14), holding at heat for not less than 3 hr, and cooling in air

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no intent to adhere to any SAE standard or recommended practice, and no commitment to conform, to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."