



AEROSPACE MATERIAL SPECIFICATION

AMS5793™**REV. C**

Issued	1998-09
Revised	2006-08
Reaffirmed	2018-10
Stabilized	2024-04

Superseding AMS5793B

Powder, Plasma Spray
95Ni - 5Al

RATIONALE

AMS5793C has been declared "STABILIZED" by SAE AMS Committee F Corrosion and Heat Resistant Alloys. This document will no longer be updated and may no longer represent standard industry practice. This document was stabilized because the document contains mature technology that is not expected to change and thus no further revisions are anticipated.

Previously this document was reaffirmed. The last technical update of this document occurred in October 2006. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub-tier supplier and not the cognizant engineering organization.

STABILIZED NOTICE

AMS5793C has been declared "STABILIZED" by SAE AMS Committee F Corrosion and Heat Resistant Alloys and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

For more information on this standard, visit

<https://www.sae.org/standards/content/AMS5793C/>

SAE WEB ADDRESS:

1. SCOPE

1.1 Form

This specification covers a nickel-aluminum aggregate in the form of powder.

1.2 Application

This powder has been used typically as an undercoat for plasma spray coatings, as a constituent in plasma spray powders, or for dimensional buildup, but usage is not limited to such applications.

1.3 Classification

Powder supplied to this specification is classified as follows:

Type 1 - Prealloyed powder, produced by atomization of 95% Nickel, 5% Aluminum alloy.

Type 2 - Composite powder, produced by cladding fine aluminum particles to a textured nickel core powder with the use of a suitable binder system.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAENORM.COM : Click to view the full PDF of AMS5793C

2.1 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, or www.astm.org.

ASTM B 214	Sieve Analysis of Granular Metal Powders
ASTM B 215	Sampling Finished Lots of Metal Powders
ASTM C 117	Material Finer Than 75- μ m (No. 200) Sieve in Mineral Aggregates by Washing
ASTM E 1473	Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

The powder shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 1473, spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Aluminum	4.0	5.5
Impurities, Total (3.1.1)	--	2.50
Nickel	remainder	

3.1.1 Applicable to Type 2 powder only, shall be present as volatile phenolic binder.

3.2 Properties

Powder shall conform to the following requirements:

3.2.1 Particle Size Determination

Powder shall be supplied with the particle size distribution shown in Table 2. Sieve analysis shall be conducted in accordance with ASTM B 214 or ASTM C 117; the method of testing used shall be reported.

TABLE 2 - MINIMUM PARTICLE SIZE DETERMINATION

U.S. Sieve Size	% by weight min	% by weight max
Retained on No. 140 (106 μ m)	--	0.5
Retained on No. 170 (90 μ m)	--	5.0
Retained on No. 325 (45 μ m)	90	--

3.2.2 Flowability

Powder shall be visually examined for free flowing through a suitable powder feeder and spray gun. The powder stream shall allow the flow to be consistent and without excessive pulsation.

3.2.3 Plasma Spraying

Powder shall produce acceptable plasma spray coatings; standards for acceptance and method of test may be agreed upon by purchaser and vendor.

3.3 Quality

Powder, as received by purchaser, shall be thoroughly blended, uniform in color and quality, dry, and free from foreign materials and from imperfections detrimental to its spraying qualities.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of powder shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the powder conforms to specified requirements.

4.2 Classification of Tests

All technical requirements are acceptance tests and preproduction tests and shall be performed prior to or on the initial shipment of powder to a purchaser, on each lot, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing

4.3.1 Shall be in accordance with ASTM B 215: sufficient powder shall be taken from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 A lot shall be all powder produced in a single production run from the same batch of raw materials under the same fixed conditions and presented for vendor's inspection at one time.

4.3.1.2 When a statistical sampling plan has been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.5 shall state that such plan was used.

4.4 Approval

4.4.1 Sample powder shall be approved by purchaser before powder for production use is supplied, unless such approval is waived by purchaser. Results of tests on production powder shall be essentially equivalent to those on the approved sample powder.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production powder that are essentially the same as those used on the approved sample powder. If necessary to make any change in ingredients, in type of equipment for processing, in manufacturing or inspection procedures, vendor shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample powder. Production powder made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports

The vendor of powder shall furnish for each lot a report showing the composition, the method of testing used to determine particle size, and stating that the powder conforms to the other technical requirements. This report shall include the purchase order number, lot number, AMS 5793C, vendor's powder designation, and quantity.

4.6 Resampling and Retesting

If any specimen used in the above tests fails to meet the specified requirements, disposition of the powder may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the powder represented. Results of all tests shall be reported.