



AEROSPACE MATERIAL SPECIFICATION

AMS6299**REV. F**Issued 1964-01
Revised 2014-02

Superseding AMS6299E

Steel Bars, Forgings, and Tubing, Carburizing
0.50Cr - 1.8Ni - 0.25Mo (0.17 - 0.23C) (SAE 4320H)
(Composition similar to UNS H43200)

RATIONALE

AMS6299F results from a Five Year Review and update of this specification

1. SCOPE

1.1 Form

This specification covers an aircraft-quality, low-alloy steel in the form of bars, forgings, mechanical tubing, and forging stock.

1.2 Application

These products have been used typically for parts to be carburized requiring high minimum core hardness with wide range in sections 0.375 inch (9.5 mm) and under in thickness, but usage is not limited to such applications. The core may or may not be machinable after hardening.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2251	Tolerances, Low-Alloy Steel Bars
AMS2253	Tolerances, Carbon and Alloy Steel Tubing
AMS2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS2301	Steel Cleanliness, Aircraft Quality, Magnetic Particle Inspection Procedure

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS6299F>**

AMS2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel, Wrought Products and Forging Stock
AMS2372	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Forgings
AMS2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification, Forgings
AS1182	Standard Stock Removal Allowance, Aircraft-Quality and Premium-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 255	Determining Hardenability of Steel
ASTM A 370	Mechanical Testing of Steel Products
ASTM E 112	Determining Average Grain Size
ASTM E 350	Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
ASTM E 381	Macroetch Testing Bars, Billets, Blooms, and Forgings

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350 or by spectrographic or other analytical methods approved by purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	0.17	0.23
Manganese	0.40	0.70
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.35	0.65
Nickel	1.55	2.00
Molybdenum	0.20	0.30
Copper	--	0.35

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2259.

3.2 Condition

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

3.2.1 Bars

3.2.1.1 Bars 0.500 Inch (12.70 mm) and Under in Nominal Diameter or Least Distance Between Parallel Sides

Cold finished having tensile strength not higher than 125 ksi (860 MPa) or hardness not higher than 262 HB, or equivalent (See 8.2).

3.2.1.2 Bars Over 0.500 Inch (12.70 mm) in Nominal Diameter or Least Distance Between Parallel Sides

Hot finished and annealed, unless otherwise ordered, having hardness not higher than 229 HB, or equivalent (See 8.2). Bars ordered cold finished may have hardness as high as 248 HB, or equivalent (See 8.2).

3.2.1.3 Bar shall not be cut from plate (Also see 4.4.2).

3.2.2 Forgings

As ordered.

3.2.3 Mechanical Tubing

Cold finished, unless otherwise ordered, having hardness not higher than 25 HRC, or equivalent (See 8.2). Tubing ordered hot finished and annealed shall have hardness not higher than 99 HB, or equivalent (See 8.2).

3.2.4 Forging Stock

As ordered by the forging manufacturer.

3.3 Properties

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

3.3.1 Macrostructure

Visual examination of transverse full cross-sections from bars, billets, tube rounds and forging stock, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E 381 shown in Table 2.

TABLE 2 - MACROSTRUCTURE LIMITS

Square Inches	Square Centimeters	Macrographs
Up to 36, incl	Up to 230, incl	S2 - R1 - C2
Over 36 to 133, incl	Over 230 to 858, incl	S2 - R2 - C3
Over 133	Over 858	Note 1

Note 1 Limits for larger sizes shall be agreed upon by purchaser and vendor. The purchaser shall have written approval of the agreement from the cognizant engineering organization.

3.3.1.1 If tubes are produced directly from ingots or large blooms, transverse sections may be taken from the tubes rather than tube rounds. Macroetch standards for such tubes shall be agreed upon by purchaser and vendor.

3.3.2 Average Grain Size

Shall be ASTM 5 or finer determined in accordance with ASTM E 112.

3.3.3 Hardenability

Shall be J1/16 inch (1.5 mm) = HRC 48 maximum and J4/16 (6 mm) = 32 HRC minimum, determined on the standard end-quench test specimen in accordance with ASTM A 255, except that the steel shall be normalized at 1675 °F ± 10 (915 °C ± 6) and the test specimen austenitized at 1500 °F ± 10 (815 °C ± 6).

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.4.1 Steel shall be aircraft quality conforming to AMS2301.

3.4.2 Bars and tubing ordered hot rolled or cold drawn, or ground, turned, or polished, shall, after removal of the standard stock removal allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the machined, ground, turned, or polished surface.

3.4.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.5 Tolerances

Shall be as follows:

3.5.1 Bars

In accordance with AMS2251.

3.5.2 Mechanical Tubing

In accordance with AMS2253.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), condition (3.2), macrostructure (3.3.1), average grain size (3.3.2), hardenability (3.3.3), frequency-severity cleanliness rating (3.4.1), and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Grain flow of die forgings (3.4.3) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be as follows:

4.3.1 Bars, Mechanical Tubing, and Forging Stock

In accordance with AMS2370.

4.3.2 Forgings

In accordance with AMS2372.