

AEROSPACE
MATERIAL
SPECIFICATION

AMS 7855A
Superseding AMS 7855

Issued 3-15-66
Revised 10-1-84

COLUMBIUM ALLOY BARS, RODS, AND WIRE
10W - 2.5Zr
Recrystallized

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of 10-25-83. It is recommended that this specification not be specified for new designs.

This cover sheet should be attached to the "A" revision of the subject specification.

SAENORM.COM : Click to view the full PDF of [ams7855a](#)

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.



AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

AMS 7855A

Superseding AMS 7855

Issued 3-15-66

Revised 11-1-67

COLUMBIUM ALLOY BARS, RODS, AND WIRE 10W - 2.5Zr Recrystallized

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- 2. APPLICATION:** Primarily for parts and assemblies requiring exposure at ultra high temperatures. Applications in oxidizing atmospheres necessitate a protective coating.
- 3. COMPOSITION:** The product shall conform to the following:

	min	max
Tungsten	9.0	11.0
Zirconium	2.0	3.0
Tantalum	--	0.15
Carbon	--	0.030
Silicon	--	0.02
Iron	--	0.02
Oxygen	--	0.020 (200 ppm)
Titanium	--	0.01
Nitrogen	--	0.010 (100 ppm)
Hydrogen	--	0.001 (10 ppm)
Columbium		remainder

- 3.1** When a dispute occurs between purchaser and vendor over results of tests for chemical composition, metallic elements shall be determined spectrophotographically, carbon shall be determined conductometrically, oxygen shall be determined by the vacuum fusion or conductometric method, nitrogen shall be determined by the Kjeldahl method, and hydrogen shall be determined by the vacuum extraction method.
- 4. CONDITION:** Hot-cold worked, descaled, and recrystallized or, if so specified, hot-cold worked, descaled, centerless ground, and recrystallized.
 - 4.1** The surface finish of centerless ground bars shall be 90 microinches or smoother.
- 5. TECHNICAL REQUIREMENTS:** When ASTM methods are specified for determining conformance to the following requirements, tests shall be conducted in accordance with the issue of the ASTM method listed in the latest issue of AMS 2350.
 - 5.1 Heat Treatment:** Material shall be recrystallized at a temperature between 2200 and 2400 F (1204.4 and 1315.5 C) under vacuum (less than 0.1 micron mercury) or inert atmosphere or as agreed upon by purchaser and vendor.
 - 5.2 Room Temperature Tensile Properties:** Material 0.050 - 0.500 in., incl, in diameter shall conform to the following requirements when tested at room temperature using strain rates of 0.003 - 0.007 in. per in. per min. through the yield strength and 0.03 - 0.07 in. per in. per min. above the yield strength.

Tensile Strength, psi	75,000 min
Yield Strength at 0.2% Offset, psi	60,000 min
Elongation, % in 1 in.	20 min
Reduction of Area (round specimens), %	30 min

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or to accept any recommendation, practice, or procedure recommended by the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 5.2.1 Properties of round rods and wire under 0.050 in. and over 0.500 in. in diameter and of all bars, rods, and wire other than round shall be as agreed upon by purchaser and vendor.
- 5.3 **Hardness:** Shall be not higher than Vickers 225 or equivalent.
- 5.4 **Microstructure:** Material recrystallized as in 5.1 shall show a structure consisting essentially of recrystallized grains; standards for acceptance shall be as agreed upon by purchaser and vendor.
- 5.5 **Tensile Properties at 2200 F (1204.4 C):** Material 0.050 - 0.500 in. , incl, in diameter shall be capable of meeting the following requirements. Tensile test specimens shall be heated to 2200 F \pm 10 (1204.4 C \pm 5.6) under vacuum (less than 0.1 micron mercury) or an inert atmosphere, held at heat for 15 min. before testing, and tested at 2200 F \pm 10 (1204.4 C \pm 5.6) at a strain rate of 0.03 - 0.07 in. per in. in accordance with ASTM E21.

Tensile Strength, psi	25,000 min
Yield Strength at 0.2% Offset, psi	20,000 min
Elongation, % in 1 in.	20 min

- 5.5.1 Properties of round rods and wire under 0.050 in. and over 0.500 in. in diameter and of all bars, rods, and wire other than round shall be as agreed upon by purchaser and vendor.
- 6. **QUALITY:** Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. **TOLERANCES:**

7.1 **Hot-Cold Worked and Descaled:**

7.1.1 **Round Rod and Wire:**

Nominal Diameter Inches	Tolerance, Inch		Out of Round Inch
	plus	minus	
0.016 to 0.030, incl	0.0005	0.0005	--
Over 0.030 to 0.062, incl	0.001	0.001	--
Over 0.062 to 0.281, incl	0.002	0.002	0.004
Over 0.281 to 0.422, incl	0.010	0.005	0.008
Over 0.422 to 0.625, incl	0.010	0.005	0.012
Over 0.625 to 0.875, incl	0.015	0.005	0.015
Over 0.875 to 1.000, incl	0.020	0.005	0.015
Over 1.000 to 1.375, incl	0.020	0.010	0.018
Over 1.375 to 1.500, incl	0.020	0.015	0.020
Over 1.500 to 1.625, incl	0.025	0.015	0.020
Over 1.625 to 2.000, incl	0.030	0.020	0.025
Over 2.000 to 2.500, incl	0.032	0.032	0.025
Over 2.500 to 3.250, incl	0.032	0.032	0.027
Over 3.250 to 3.500, incl	0.045	0.045	0.040

7.1.2 **Square and Rectangular Bar:**

Nominal Thickness (T) Inches	Thickness Tolerance, Inch		Width Tolerance, Inch	
	plus and minus		plus	minus
0.187 to 0.500, incl	0.10T		10%	0
Over 0.500	0.062		10%	0