

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE

MAM 2241B

Issued JAN 1983
Revised JAN 1996

Superseding MAM 2241A

TOLERANCES, METRIC Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

1. SCOPE:

This specification covers established metric manufacturing tolerances applicable to corrosion and heat resistant steel, iron alloy, titanium, and titanium alloy bars and wire ordered to metric dimensions. These tolerances apply to all conditions, unless otherwise noted. The term "excl" is used to apply only to the higher figure of the specified range.

1.1 AMS 2241 is the inch/pound version of this MAM.

2. DIAMETER, THICKNESS, AND WIDTH:

2.1 Cold Finished Bars:

2.1.1 Rounds, Squares, Hexagons, and Octagons (See 2.1.3): See Table 1.

TABLE 1 - Diameter or Thickness Tolerances

Specified Diameter or Thickness Millimeters	Tolerance, Millimeter Plus and Minus (See 2.1.1.1) Rounds	Tolerance, Millimeter Minus Only (See 2.1.1.2) Squares, Hexagons, and Octagons
Over 12.50 to 25.00, excl	0.05	0.10
25.00	0.062	0.10
Over 25.00 to 37.50, excl	0.026	0.15
37.50 to 50.00, incl	0.08	0.15
Over 50.00 to 75.00, incl	0.08	0.20
Over 75.00 to 100.00, incl	0.08	0.25

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1996 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

2.1.1.1 Size tolerances for round bars are plus and minus as shown in Table 1. When required, however, they may be specified all plus and nothing minus, or all minus and nothing plus, or any combination of plus and minus, if the total spread in size tolerance for a specified size is not less than the total spread shown in Table 1.

2.1.1.2 For titanium and titanium alloys, the difference among the three measurements of the distance between opposite faces of hexagons shall be not greater than one-half the size tolerance and the difference among the measurements of the distance between opposite faces of octagons shall be not greater than the size tolerance.

2.1.2 Flats (See 2.1.3): See Table 2.

TABLE 2 - Thickness and Width Tolerances

Specified Width Millimeters			Thickness and Width Tolerance, Millimeter Plus and Minus
3.00	to	25.00, incl	0.05
Over 25.00	to	50.00, incl	0.08
Over 50.00	to	75.00, incl	0.10
Over 75.00	to	115.00, incl	0.12

2.1.2.1 For thickness 6.0 millimeters and under, thickness tolerances shall be double those in Table 2.

2.1.3 If cold finished bars are ordered heat treated or heat treated and pickled after cold finishing, tolerances shall be double those of Table 1 and Table 2.

2.2 Cold Finished Wire:

2.2.1 Rounds, Squares, Hexagons, and Octagons (See 2.2.1.1): See Table 3.

TABLE 3 - Diameter or Thickness Tolerances

Specified Diameter or Thickness Millimeters	Tolerance, Millimeter Plus and Minus Rounds and Squares	Tolerance, Millimeter Minus Only (See 2.2.1.3)	
		Hexagons and Octagons	
0.08 to 0.12, excl	0.002	--	
0.12 to 0.20, excl	0.005	--	
0.20 to 0.30, excl	0.008	--	
0.30 to 0.60, excl	0.010 (See 2.2.1.2)	--	
0.60 to 0.85, excl	0.012 (See 2.2.1.2)	--	
0.85 to 1.10, excl	0.020	--	
1.10 to 3.15, excl	0.02	--	
3.15 to 7.80, excl	0.02	0.05	
7.80 to 12.50, excl	0.038	0.08	
12.50	0.05	0.10	

2.2.1.1 If cold finished wire is ordered heat treated or heat treated and pickled after cold finishing, tolerances shall be double those of Table 3 for nominal sizes 0.60 millimeter and over.

2.2.1.2 For titanium and titanium alloys, tolerances for these sizes are ± 0.019 millimeter.

2.2.1.3 For titanium and titanium alloys, the difference among the three measurements of the distance between opposite faces of hexagons shall be not greater than one-half the size tolerance and the difference among the four measurements of the distance between opposite faces of octagons shall be not greater than one-half the size tolerance.

2.2.1.4 Out-of-Round: Round wire shall not be out-of-round by more than one-half of the total tolerance shown in Table 3.

2.2.2 Flats: See Table 4.

TABLE 4 - Thickness Tolerances

Specified Thickness Millimeters	Tolerance, Millimeter Plus and Minus
Up to 0.70, excl	0.02
0.70 to 0.90, excl	0.038
0.90 to 4.75, excl	0.04

2.2.2.1 Width tolerances shall be ± 0.12 millimeter for specified widths 1.56 to 9.38 millimeters, exclusive.

2.3 Hot Finished Bars:

2.3.1 Hot Rolled:

2.3.1.1 Rounds and Squares: See Table 5. Out-of-round is the difference between the maximum and minimum diameters of the bar, measured at the same cross section. Out-of-square is the difference in the two dimensions at the same cross section of a square bar, each dimension being the distance between opposite faces.

TABLE 5 - Diameter or Thickness Tolerances

Specified Diameter or Thickness Millimeters			Tolerance Millimeters Plus	Tolerance Millimeter Minus	Out-of-Round or Out-of-Square Millimeters
	6.25	to 7.80, incl	0.12	0.12	0.20
Over	7.80	to 11.00, incl	0.15	0.15	0.22
Over	11.00	to 15.75, incl	0.18	0.18	0.25
Over	15.75	to 22.00, incl	0.20	0.20	0.30
Over	22.00	to 25.00, incl	0.22	0.22	0.32
Over	25.00	to 28.00, incl	0.25	0.25	0.38
Over	28.00	to 31.00, incl	0.28	0.28	0.40
Over	31.00	to 34.00, incl	0.30	0.30	0.45
Over	34.00	to 37.50, incl	0.35	0.35	0.52
Over	37.50	to 50.00, incl	0.40	0.40	0.58
Over	50.00	to 62.50, incl	0.80	0	0.58
Over	62.50	to 87.50, incl	1.20	0	0.88
Over	87.50	to 115.00, incl	1.60	0	1.15
Over	115.00	to 138.00, incl	2.00	0	1.45
Over	138.00	to 165.00, incl	3.15	0	1.75
Over	165.00	to 200.00, incl	3.90	0	2.12

2.3.1.2 Hexagons and Octagons: See Table 6.

TABLE 6 - Thickness Tolerances

Specified Thickness Millimeters		Tolerance Millimeters Plus and Minus	Maximum Difference 3 Measurements Hexagons Only Millimeters
	6.25 to 12.50, incl	0.18	0.28
Over	12.50 to 25.00, incl	0.25	0.38
Over	25.00 to 37.50, incl	0.52	0.62
Over	37.50 to 50.00, incl	0.78	0.78
Over	50.00 to 62.50, incl	1.18	1.18
Over	62.50 to 87.50, incl	1.56	1.56

2.3.1.3 Flats: See Table 7 and Table 8.

TABLE 7 - Thickness Tolerances, Millimeters; For Thickness Ranges, Millimeters

Specified Width Millimeters	3.10 to 12.50, Incl Plus and Minus	Over 12.50 to 25.00, Incl Plus and Minus	Over 25.00 to 50.00, Incl Plus and Minus	Over 50.00 to 100.00, Incl Plus	Over 50.00 to 100.00, Incl Minus	Over 100.00 to 150.00, Incl Plus	Over 100.00 to 150.00, Incl Minus	Over 150.00 to 200.00, Incl Plus	Over 150.00 to 200.00, Incl Minus
Up to 25.00, incl	0.20	0.25	--	--	--	--	--	--	--
Over 25.00 to 50.00, incl	0.30	0.38	0.78	--	--	--	--	--	--
Over 50.00 to 100.00, incl	0.38	0.50	0.78	1.55	0.78	--	--	--	--
Over 100.00 to 150.00, incl	0.38	0.50	0.78	1.55	0.78	2.32	1.55	--	--
Over 150.00 to 200.00, incl	0.40	0.62	0.78	1.55	0.78	2.32	1.55	3.12	3.90
Over 200.00 to 250.00, incl	0.52	0.78	0.78	1.55	0.78	2.32	1.55	3.12	3.90

TABLE 8 - Width Tolerances

Specified Width Millimeters	Tolerance, Millimeters	
	Plus	Minus
Up to 25.00, incl	0.38	0.38
Over 25.00 to 50.00, incl	0.78	0.78
Over 50.00 to 100.00, incl	1.55	0.78
Over 100.00 to 150.00, incl	2.32	1.55
Over 150.00 to 200.00, incl	3.12	3.90
Over 200.00 to 250.00, incl	3.90	4.68

2.3.2 Forged: Tolerances shall be as agreed upon by purchaser and vendor.

3. LENGTH:

Tolerances in Table 9 and Table 10 shall apply only when definite lengths are ordered.

3.1 Hot or Cold Finished Bars:

See Table 9.