

**AEROSPACE  
MATERIAL  
SPECIFICATION**

Issued APR 1984  
Revised MAY 2001  
Noncurrent MAR 2003

Superseding MAM 2300B

**Steel Cleanliness, Premium Aircraft-Quality  
Magnetic Particle Inspection Procedure  
Metric (SI) Measurement**

**NONCURRENCY NOTICE**

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of March, 2003. It is recommended, therefore, that this specification not be specified for new designs.

AMS 2300 covers the same requirements.

"NONCURRENT" refers to those materials which have been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs.

"NONCURRENT" specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of MAM2300C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 Society of Automotive Engineers, Inc.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)

Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: [custsvc@sae.org](mailto:custsvc@sae.org)

<http://www.sae.org>

**SAE WEB ADDRESS:**

## 1. SCOPE:

1.1 This specification covers steel cleanliness requirements in metric (SI) units for premium aircraft-quality ferromagnetic steels, other than hardenable, corrosion-resistant steels, by magnetic particle inspection methods.

1.1.1 AMS 2300 is the inch/pound version of this MAM.

## 1.2 Application:

This procedure has been used typically for the cleanliness evaluation of blooms, billets, tube rounds, stock for forging or flash welded rings, slabs, bars, sheet, plate, tubing, and extrusions used in fabricating highly stressed parts where very strict magnetic particle inspection standards are used in final inspection of such parts, but may be used for qualification of a heat, melt or lot of steel.

## 2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

### 2.1 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 604 Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets  
ASTM E 10 Brinell Hardness of Metallic Materials  
ASTM E 1444 Magnetic Particle Examination

### 2.2 ANSI Publications:

Available from American National Standards Institute, Inc., 11 West 42nd Street, New York, NY 10036-8002.

ANSI B46.1 Surface Texture

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Melting Practice:

If the material specification does not require a specific method or methods of consumable electrode remelting and the purchaser has not authorized an alternate method, steel supplied to this specification shall be produced using only the vacuum arc consumable electrode process in the remelt cycle, except that steel cast as rectangular ingots for slab and plate may be produced by electrosag remelting.

### 3.2 Specimen Preparation:

3.2.1 Heat Qualification: Sampling shall be in accordance with 4.3.1, 4.3.2, or 4.3.3. Samples shall be converted into test specimens in accordance with 3.2.3.

3.2.2 Product Qualification: Product from a heat not qualified based on sampling as in 4.3.1, 4.3.2, or 4.3.3 shall be sampled in accordance with 4.3.4. Samples shall be converted into test specimens in accordance with 3.2.3.

### 3.2.3 Working and Rough Machining:

3.2.3.1 Solid Product 300 mm and Over in Nominal Diameter or Distance Between Parallel Sides: A quarter section shall be cut from each sample sufficiently oversize that the center of the original sample will be approximately on the surface of the specimen after generating to test size. The quartered section shall then be forged to a 75 to 150 mm round or square, maintaining the axis of the forging approximately parallel to original direction of rolling. As an alternate method, the full section may be rolled or forged to a 150 mm round or square and an oversize quarter obtained as in 3.2.3.3. Specimens shall be rough machined to a "one-step" straight cylinder nominally 125 mm long. Minimum stock removal shall be consistent with the machining allowance specified in 3.2.4.1.

3.2.3.2 Solid Product Over 150 to 300 mm, Exclusive in Nominal Diameter or Distance Between Parallel Sides Except Slabs and Plates: A quarter section shall be cut from each sample sufficiently oversize that the center of the original sample will be approximately on the surface of the specimen after generating to test size. The quarter section shall be converted into a test specimen by machining, or forging and machining, to a 75 to 150 mm round or square. Specimens shall be rough machined to a "one-step" straight cylinder nominally 125 mm long. Minimum stock removal shall be consistent with the machining allowance specified in 3.2.4.1.

3.2.3.3 Solid Product 150 mm and Under in Nominal Diameter or Distance Between Parallel Sides Except Flat Bars, Slabs, and Plates: A quarter section shall be cut from each sample sufficiently oversize that the center of the original sample will be approximately on the surface of the specimen after generating to test size. The quarter section shall be converted into a test specimen by machining to a "one-step" straight cylinder nominally 125 mm long. Minimum stock removal shall be consistent with the machining allowance specified in 3.2.4.1.

3.2.3.3.1 As an alternate method, a stepdown specimen may be generated from the full cross-section in equal circumferential steps as in Table 1.

TABLE 1 - Stepdown Specimens, Cylindrical

Nominal Diameter or Distance Between Parallel Sides Millimeters	Step Length Millimeters	Step Diameter 1	Step Diameter 2	Step Diameter 3	Step Diameter 4	Step Diameter 5
6.25 to 12.50, incl	125.00	D	--	--	--	--
Over 12.50 to 18.75, incl	62.50	D	2/3D	--	--	--
Over 18.75 to 25.00, incl	41.62	D	3/4D	1/2D	--	--
Over 25.00 to 37.50, incl	31.25	D	4/5D	3/5D	2/5D	--
Over 37.50	25.00	D	4/5D	3/5D	2/5D	1/5D

D = Original diameter or distance between parallel sides minus machining stock removed.

- 3.2.3.4 Flat Bars: Specimens, nominally 125 mm long, shall be rough machined to equal-length steps across the width of the specimen in accordance with Table 2, allowing 20% of the thickness or 2.50 mm, whichever is less, for minimum stock removal. Allowance of 0.25 mm shall be made for finish machining.

TABLE 2 - Stepdown Specimens, Flat Bar

Nominal Thickness Millimeters	Step Length Millimeters	Step Thickness 1	Step Thickness 2	Step Thickness 3	Step Thickness 4	Step Thickness 5
Up to 6.25, incl	125.00	T	--	--	--	--
Over 6.25 to 12.50, incl	62.50	T	2/3T	--	--	--
Over 12.50 to 25.00, incl	31.25	T	3/4T	1/2T	1/4T	--
Over 25.00	25.00	T	4/5T	3/5T	2/5T	1/5T

T = Original nominal thickness minus machining stock removed.

- 3.2.3.5 Slabs or Plates: A straight cylindrical or rectangular specimen shall be machined, or forged and machined, from each slab or plate to be tested. The specimen shall be taken essentially parallel to the direction of rolling at the center of the slab or plate width and thickness and shall be nominally 125 mm in length and not more than 100 mm in final diameter or thickness.
- 3.2.3.5.1 Product Up to 100 mm, Inclusive, in Nominal Thickness: A straight cylindrical specimen shall represent the full thickness consistent with the machining allowance specified in 3.2.4.1.
- 3.2.3.5.2 Product Over 100 to 200 mm, Inclusive, in Nominal Thickness: A straight cylindrical specimen shall represent surface to mid-thickness consistent with the machining allowance specified in 3.2.4.1.

3.2.3.5.3 Product Over 200 mm in Nominal Thickness: A straight cylindrical specimen shall be taken so that the axis is approximately midway between the surface and mid-thickness, and shall have a diameter equal to one-third the nominal thickness of the section.

3.2.3.6 Tubing:

3.2.3.6.1 Nominal Wall Thickness 6.25 mm and Over: Specimens, nominally 125 mm long, shall be rough machined to four equal circumferential steps, T, 3/4T, 1/2T, and 1/4T, allowing 2.50 mm on the diameter for stock removal. Allowance of 0.25 mm on the radii for finish machining shall be made. T = nominal wall thickness minus the machining allowance.

3.2.3.6.2 Nominal Wall Thickness Under 6.25 mm: Specimens, nominally 125 mm long, after heat treatment as in 3.2.5, shall have 10% of the wall thickness or 0.38 mm, whichever is less, removed from the outer diameter and be tested as a straight cylinder.

3.2.4 Machining:

3.2.4.1 Product Other Than Flat Bars, Slabs, and Plates Over 8 Inches Thick, and Tubing: The converted sample shall be machined to conform to the allowance of Table 3 for surface removal, allowing 0.25 mm per side for finish machining after heat treatment.

TABLE 3 - Stock Removal

Nominal Diameter or Distance Between Parallel Sides Millimeters	Minimum Stock Removal Millimeters per Side
6.25 to 12.50, incl	0.75
Over 12.50 to 18.75, incl	1.15
Over 18.75 to 25.00, incl	1.50
Over 25.00 to 37.50, incl	1.90
Over 37.50 to 50.00, incl	2.25
Over 50.00 to 62.50, incl	3.20
Over 62.50 to 87.50, incl	4.00
Over 87.50 to 112.50, incl	4.75
Over 112.50 to 150.00, incl	6.25

3.2.5 Heat Treatment: Rough machined specimens shall, if necessary, be heat treated by suitably austenitizing, quenching, and tempering or by solution and precipitation heat treating to produce hardness of 248 to 352 HB or appropriate lower hardness for steel of low hardenability. Hardness testing shall be in accordance with ASTM E 10. Specimens shall be austenitized in a neutral or slightly reducing atmosphere. Following heat treatment, surface scale may be removed by grit blasting or other acceptable method.

3.2.6 Finish Machining: The heat treated specimens shall be finished machined to surface roughness not greater than 0.8 micrometers AA, determined in accordance with ANSI B46.1. The ends of the specimen shall be finished to provide good electrical contact.

3.3 Inspection:

Magnetic particle inspection shall be performed in accordance with ASTM E 1444 by the circular, wet, continuous method (See 8.5) using 32 to 48 A/mm of diameter. If a stepdown bar is used, the smallest step shall be magnetized and inspected first; the larger steps shall be magnetized and inspected individually in succession of increasing size until all steps have been evaluated. If a longitudinal slice from slab or plate, as in 3.2.3.5 is used, only the longitudinal surfaces perpendicular to the two faces of the slab or plate shall be inspected.

3.3.1 Cleanliness standards presented herein govern nonmetallic inclusions only (See 8.5). Steel which, during inspection, reveals indications representing actual ruptures, such as cracks, seams, laminations, and laps, will be subject to rejection except where these defects result from sample preparation.

3.3.2 The results of the magnetic particle inspection shall be appropriately recorded. All recorded results shall be identified, filed, and made available to purchaser upon request.

3.4 Evaluation of Steel Cleanliness:

After inspection, each indication 0.4 mm and over shall be recorded on an inspection chart. All recorded results shall be identified, filed, and, upon request, made available to purchaser. Records shall be available for at least three years after shipment of the product. The frequency rating (F) (number) and the severity rating (S) (length) of the indications shall be calculated as follows:

3.4.1 Frequency (F):

3.4.1.1 The number of indications per test specimen is totaled.

3.4.1.2 The frequency per specimen is determined by dividing 6.45 times the total number of indications for each specimen by the test surface area of the specimen in square centimeters.

3.4.1.3 The frequency ratings for all test specimens from a heat are totaled.

3.4.1.4 The average frequency (F) equals the total frequency rating for all test specimens from a heat divided by the number of test specimens.

3.4.2 Severity (S):

3.4.2.1 The length of each indication is recorded.

3.4.2.2 The product for each specimen is computed by totaling the product of the number of indications times the appropriate progression factor shown in Table 4:

TABLE 4 - Progression Factor for Severity Rating

Length of Indication Millimeters	Progression Factor
0.4 to 0.8, excl	13
0.8 to 1.6, excl	26
1.6 to 3.2, excl	103
3.2 and over	1650

- 3.4.2.3 The severity per specimen is determined by dividing the product for each specimen by the test surface area of the specimen in square centimeters.
- 3.4.2.4 The severity ratings for all test specimens from a heat are totaled.
- 3.4.2.5 The average severity (S) equals the total severity rating for all test specimens from a heat divided by the number of test specimens.

### 3.5 Disposition:

Product inspected in accordance with this specification shall conform to one of the following requirements as applicable:

- 3.5.1 Product inspected for heat qualification as in 4.3.1, 4.3.2, or 4.3.3, and for product qualification as in 4.3.4 shall conform to a maximum average frequency rating (F) of 0.25 and a maximum average severity rating (S) of 0.50.
- 3.5.2 Product inspected for heat qualification as in 4.3.1.2 shall conform to a maximum average frequency rating (F) of 0.10 and a maximum average severity rating (S) of 0.20 and, in addition, specimens as in 4.3.1.2.2, macroetched in accordance with ASTM A 604, shall meet the macrostructure requirements of the applicable material specification.
- 3.5.3 Product inspected in accordance with this specification and having a frequency-severity rating exceeding the specified limits may be re-evaluated for specific applications when permitted by purchaser. Evaluation of any one or two steps of stepdown specimens may be waived by purchaser when the area represented is not considered critical for the end product

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

#### 4.2 Classification of Tests:

All applicable technical requirements are acceptance tests and shall be performed as specified in 4.2.1 or 4.2.2.

4.2.1 Heat Qualification: Tests of samples taken as in 4.3.1, 4.3.2, or 4.3.3 to determine conformance to "heat qualification" requirements, if acceptable, need be conducted only once per heat.

4.2.1.1 Heats which have been qualified as semi-finished product shall be considered qualified for finished product.

4.2.2 Product Qualification: Tests on product not "heat qualified" shall be conducted on product of each size and shape of each lot made from each heat.

#### 4.3 Sampling and Testing:

One of the sampling procedures described in 4.3.1, 4.3.2, or 4.3.3 shall be performed by the producer for heat qualification; the procedure used shall be at the producer's option. No further sampling by the producer shall be required from a heat which meets the requirements of 3.5. For product not heat qualified as in 4.3.1, 4.3.2, or 4.3.3, sampling procedures shall be as described in 4.3.4.

4.3.1 For Heat Qualification of Heats Produced From Top Poured Electrodes: Samples shall be taken from semi-finished or finished product in accordance with the sampling plan of either 4.3.1.1 or 4.3.1.2.

4.3.1.1 First Option:

4.3.1.1.1 For heats having four remelted ingots or less, or for portions of heats within this limit, samples shall be taken to represent remelted material that relates to the bottom of the first electrode and the top of the last electrode of the heat.

4.3.1.1.2 For heats having five through nine remelted ingots, inclusive, or for portions of heats within these limits, samples shall be taken to represent the top and bottom of the first and last remelted ingots.

4.3.1.1.3 For heats having ten or more remelted ingots, samples shall be taken to represent the top and bottom of the first, middle, and last remelted ingots.

4.3.1.2 Second Option (See 3.5.2):

4.3.1.2.1 For all heats, regardless of the number of remelted ingots, samples shall be taken from remelted material representing the top of one electrode and the bottom of one electrode of the heat.